



Ultramid® B3EG6

BASF Corporation - Polyamide 6

Monday, November 4, 2019

General Information

Product Description

Ultramid B3EG6 is a 30% glass fiber reinforced injection molding PA6 grade.

Applications

Typical applications include industrial articles and electrical insulating parts.

General

Material Status	• Commercial: Active
Availability	• Asia Pacific • Europe • North America
Filler / Reinforcement	• Glass Fiber, 30% Filler by Weight
Features	• Oil Resistant
Uses	• Electronic Insulation • Industrial Applications
Agency Ratings	• EC 1907/2006 (REACH)
RoHS Compliance	• RoHS Compliant
Automotive Specifications	• FORD WSK-M4D664-A • GM GMW16582P-PA6-GF30 Color: Black • FORD WSS-M4D664-B1 • GM GMW16582P-PA6-GF30 Color: Natural
Forms	• Pellets
Processing Method	• Injection Molding

ASTM & ISO Properties ¹

Physical	Dry	Conditioned	Unit	Test Method
Density / Specific Gravity	1.36	--		ASTM D792
Density	1.36	--	g/cm ³	ISO 1183
Melt Volume-Flow Rate (MVR)				ISO 1133
275°C/5.0 kg	50	--	cm ³ /10min	
Molding Shrinkage - Flow (0.125 in)	3.0E-3	--	in/in	
Water Absorption (Saturation)	6.6	--	%	ASTM D570
Water Absorption				ISO 62
Saturation, 73°F	6.6	--	%	
Water Absorption				ASTM D570
Equilibrium, 50% RH	2.1	--	%	
Water Absorption				ISO 62
Equilibrium, 73°F, 50% RH	2.1	--	%	
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus (73°F)	1.38E+6	899000	psi	ISO 527-2
Tensile Strength (Break, 73°F)	24900	--	psi	ASTM D638
Tensile Stress (Break, 73°F)	26800	16700	psi	ISO 527-2
Tensile Elongation (Break, 73°F)	3.2	--	%	ASTM D638
Tensile Strain (Break, 73°F)	3.5	8.0	%	ISO 527-2
Flexural Modulus (73°F)	1.20E+6	--	psi	ASTM D790
Flexural Modulus (73°F)	1.25E+6	725000	psi	ISO 178
Flexural Stress (73°F)	39200	26100	psi	ISO 178

Ultramid® B3EG6

BASF Corporation - Polyamide 6

Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179
-22°F	5.2	--	ft·lb/in ²	
73°F	7.1	14	ft·lb/in ²	
Charpy Unnotched Impact Strength				ISO 179
-22°F	38	--	ft·lb/in ²	
73°F	45	52	ft·lb/in ²	
Notched Izod Impact				ASTM D256
-40°F	1.8	--	ft·lb/in	
73°F	2.0	--	ft·lb/in	
Notched Izod Impact Strength				ISO 180
73°F	7.1	9.5	ft·lb/in ²	
Thermal	Dry	Conditioned	Unit	Test Method
Deflection Temperature Under Load				ASTM D648
66 psi, Unannealed	428	--	°F	
Heat Deflection Temperature				ISO 75-2/B
66 psi, Unannealed	428	--	°F	
Deflection Temperature Under Load				ASTM D648
264 psi, Unannealed	410	--	°F	
Heat Deflection Temperature				ISO 75-2/A
264 psi, Unannealed	410	--	°F	
Peak Melting Temperature	428	--	°F	ASTM D3418
Melting Temperature (DSC)	428	--	°F	ISO 3146
CLTE - Flow	1.1E-5	--	in/in/°F	ASTM E831
CLTE - Flow	1.3E-5	--	in/in/°F	
CLTE - Transverse	3.6E-5	--	in/in/°F	
RTI Elec				UL 746
0.030 in	248	--	°F	
0.06 in	248	--	°F	
0.12 in	248	--	°F	
RTI Imp				UL 746
0.06 in	203	--	°F	
0.12 in	203	--	°F	
RTI Str				UL 746
0.06 in	266	--	°F	
0.12 in	266	--	°F	
Electrical	Dry	Conditioned	Unit	Test Method
Volume Resistivity (0.0591 in)	1.0E+15	1.0E+12	ohms·cm	ASTM D257
Volume Resistivity	1.0E+15	1.0E+12	ohms·cm	IEC 60093
Dielectric Constant (1 MHz)	3.80	6.80		IEC 60250
Dissipation Factor				IEC 60250
100 Hz	0.023	0.22		
1 MHz	0.023	0.22		
Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating				UL 94
0.06 in	HB	--		
0.12 in	HB	--		

Ultramid® B3EG6

BASF Corporation - Polyamide 6

Processing Information

Injection	Dry	Unit
Drying Temperature	181	°F
Drying Time	2.0 to 4.0	hr
Suggested Max Moisture	0.15	%
Processing (Melt) Temp	518 to 563	°F
Mold Temperature	176 to 203	°F
Injection Pressure	508 to 1810	psi
Injection Rate	Fast	

Notes

¹ Typical properties: these are not to be construed as specifications.