



Ultrason® E 2010 G6

BASF Corporation - Polyethersulfone

Tuesday, November 5, 2019

General Information

Product Description

Ultrason E 2010 G6 is a 30% glass reinforced, medium viscosity injection molding PESU grade with high rigidity and strength.

Applications

Typical applications include circuit breaker parts, lamp holders, heat shields, impellers, and printer cartridges.

General

Material Status	• Commercial: Active
Availability	• Asia Pacific • Europe • North America
Filler / Reinforcement	• Glass Fiber, 30% Filler by Weight
Features	• High Rigidity • High Strength • Medium Viscosity
Uses	• Electrical Parts • Printer Parts
Agency Ratings	• EC 1907/2006 (REACH)
RoHS Compliance	• RoHS Compliant
Automotive Specifications	• GM GMW15702-020661 PESU-GF30 Color: 15038 Black
Forms	• Pellets
Processing Method	• Injection Molding

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density	1.59	g/cm ³	ISO 1183
Melt Volume-Flow Rate (MVR) (360°C/10.0 kg)	25	cm ³ /10min	ISO 1133
Molding Shrinkage			ISO 294-4
Across Flow	0.58	%	
Flow	0.28	%	
Water Absorption (Saturation, 73°F)	1.6	%	ISO 62
Water Absorption (Equilibrium, 73°F, 50% RH)	0.60	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (73°F)	1.42E+6	psi	ISO 527-2
Tensile Stress (Break, 73°F)	21800	psi	ISO 527-2
Tensile Strain (Break, 73°F)	2.3	%	ISO 527-2
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179
-22°F	3.8	ft-lb/in ²	
73°F	4.5	ft-lb/in ²	
Charpy Unnotched Impact Strength			ISO 179
-22°F	29	ft-lb/in ²	
73°F	26	ft-lb/in ²	
Notched Izod Impact Strength			ISO 180
-22°F	4.5	ft-lb/in ²	
73°F	4.8	ft-lb/in ²	
Hardness	Nominal Value	Unit	Test Method
Ball Indentation Hardness	32500	psi	ISO 2039-1

Ultrason® E 2010 G6

BASF Corporation - Polyethersulfone

Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (264 psi, Unannealed)	433	°F	ISO 75-2/A
CLTE - Flow	8.3E-6	in/in/°F	
RTI Elec			UL 746
0.06 in	356	°F	
0.12 in	356	°F	
RTI Imp			UL 746
0.06 in	356	°F	
0.12 in	374	°F	
RTI Str			UL 746
0.06 in	374	°F	
0.12 in	374	°F	
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	> 1.0E+15	ohms	IEC 60093
Volume Resistivity	> 1.0E+15	ohms·cm	IEC 60093
Electric Strength	940	V/mil	IEC 60243-1
Dielectric Constant			IEC 60250
100 Hz	4.30		
1 MHz	4.30		
Dissipation Factor			IEC 60250
100 Hz	2.0E-3		
1 MHz	0.010		
Comparative Tracking Index	125	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
0.06 in	V-0		
0.12 in	V-0		

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	266 to 302	°F
Drying Time	4.0	hr
Suggested Max Moisture	0.020	%
Processing (Melt) Temp	662 to 734	°F
Mold Temperature	302 to 374	°F
Injection Pressure	508 to 1810	psi
Injection Rate	Fast	

Notes

¹ Typical properties: these are not to be construed as specifications.