



Vectra® A530

Celanese Corporation - Liquid Crystal Polymer

Sunday, November 3, 2019

General Information

Product Description

Best overall surface appearance with properties similar to A130. Less abrasive than glass fiber reinforced grades. Improved toughness over A130. Outstanding hydrolytic stability. Recommended where aesthetics are key. 30% mineral filled. Chemical abbreviation according to ISO 1043-1 : LCP. Inherently flame retardant FDA compliant UL-Listing V-0 in natural and black at 0.38mm thickness per UL 94 flame testing, and UL-5VA in natural at 3.0mm. Relative-Temperature-Index (RTI) according to UL 746B: electrical 130°C, mechanical 130°C. UL = Underwriters Laboratories (USA)

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Filler / Reinforcement	• Mineral, 30% Filler by Weight		
Features	• Flame Retardant • Good Surface Finish	• Good Toughness • Hydrolytically Stable	• Pleasing Surface Appearance
Agency Ratings	• FDA Unspecified Rating		
RoHS Compliance	• Contact Manufacturer		
Resin ID (ISO 1043)	• LCP		

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density	1.65	g/cm ³	ISO 1183
Molding Shrinkage			ISO 294-4
Across Flow	0.70	%	
Flow	0.20	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	1.60E+6	psi	ISO 527-2/1A
Tensile Stress (Break)	23200	psi	ISO 527-2/1A/5
Tensile Strain (Break)	4.6	%	ISO 527-2/1A/5
Flexural Modulus (73°F)	1.73E+6	psi	ISO 178
Flexural Stress (73°F)	26100	psi	ISO 178
Compressive Modulus	1.38E+6	psi	ISO 604
Compressive Stress (1% Strain)	8700	psi	ISO 604
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (73°F)	12	ft·lb/in ²	ISO 179/1eA
Charpy Unnotched Impact Strength (73°F)	24	ft·lb/in ²	ISO 179/1eU
Notched Izod Impact Strength (73°F)	13	ft·lb/in ²	ISO 180/1A
Unnotched Izod Impact Strength (73°F)	19	ft·lb/in ²	ISO 180/1U
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (M-Scale)	67		ISO 2039-2
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (66 psi, Unannealed)	397	°F	ISO 75-2/B
Heat Deflection Temperature (264 psi, Unannealed)	374	°F	ISO 75-2/A
Heat Deflection Temperature (1160 psi, Unannealed)	250	°F	ISO 75-2/C
Vicat Softening Temperature	304	°F	ISO 306/B50
Melting Temperature ²	536	°F	ISO 11357-3
CLTE - Flow	5.6E-6	in/in/°F	ISO 11359-2

UL and the UL logo are trademarks of UL LLC © 2019. All Rights Reserved.

The information presented here was acquired by UL from the producer of the product or material or original information provider. However, UL assumes no responsibility or liability for the accuracy of the information contained on this website and strongly encourages that upon final product or material selection information is validated with the manufacturer. This website provides links to other websites owned by third parties. The content of such third party sites is not within our control, and we cannot and will not take responsibility for the information or content.

Vectra® A530

Celanese Corporation - Liquid Crystal Polymer

Thermal	Nominal Value	Unit	Test Method
CLTE - Transverse	1.7E-5	in/in/°F	ISO 11359-2
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	> 1.0E+15	ohms	IEC 60093
Volume Resistivity	1.0E+14	ohms·cm	IEC 60093
Electric Strength	1100	V/mil	IEC 60243-1
Relative Permittivity			IEC 60250
100 Hz	3.80		
1 MHz	3.20		
Dissipation Factor			IEC 60250
100 Hz	0.010		
1 MHz	0.016		
Arc Resistance	180	sec	Internal Method
Comparative Tracking Index	200	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating	V-0		UL 94

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	302	°F
Drying Time	4.0 to 6.0	hr
Suggested Max Moisture	0.010	%
Hopper Temperature	68 to 86	°F
Rear Temperature	518 to 536	°F
Middle Temperature	527 to 545	°F
Front Temperature	536 to 554	°F
Nozzle Temperature	554 to 572	°F
Processing (Melt) Temp	545 to 563	°F
Mold Temperature	176 to 248	°F
Injection Rate	Fast	
Back Pressure	< 435	psi

Injection Notes

Feeding zone temperature: 60 to 80°C
Zone4 temperature: 285 to 295°C
Hot runner temperature: 285 to 295°C

Notes

¹ Typical properties: these are not to be construed as specifications.

² 10°C/min