



Vectra® E631i

Celanese Corporation - Liquid Crystal Polymer

Sunday, November 3, 2019

General Information

Product Description

30% glass reinforced Chemical abbreviation according to ISO 1043-1 : LCP Inherently flame retardant. UL-Listing V-0 black at 0.15mm thickness per UL 94 flame testing. UL = Underwriters Laboratories (USA)

General

Material Status	• Commercial: Active
Availability	• Africa & Middle East • Europe • Asia Pacific • Latin America • North America
Filler / Reinforcement	• Glass Fiber, 30% Filler by Weight
Features	• Flame Retardant
Resin ID (ISO 1043)	• LCP

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density	1.61	g/cm ³	ISO 1183
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2.61E+6	psi	ISO 527-2/1A
Tensile Stress (Break)	21000	psi	ISO 527-2/1A/5
Tensile Strain (Break)	1.3	%	ISO 527-2/1A/5
Flexural Modulus (73°F)	2.47E+6	psi	ISO 178
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (264 psi, Unannealed)	482	°F	ISO 75-2/A
Melting Temperature ²	635	°F	ISO 11357-3
Electrical	Nominal Value	Unit	Test Method
Relative Permittivity (1 MHz)	4.50		IEC 60250
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.0059 in)	V-0		UL 94

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	302	°F
Drying Time	6.0	hr
Suggested Max Moisture	0.010	%
Hopper Temperature	68 to 86	°F
Rear Temperature	599 to 617	°F
Middle Temperature	608 to 626	°F
Front Temperature	617 to 635	°F
Nozzle Temperature	635 to 653	°F
Processing (Melt) Temp	635 to 653	°F
Mold Temperature	176 to 248	°F
Injection Rate	Fast	
Back Pressure	< 435	psi

Vectra® E631i

Celanese Corporation - Liquid Crystal Polymer

Injection Notes

Feeding zone temperature: 60 to 80°C

Zone4 temperature: 330 to 340°C

Notes

¹ Typical properties: these are not to be construed as specifications.

² 10°C/min