



Vectra® MT1335

Celanese Corporation - Liquid Crystal Polymer

Sunday, November 3, 2019

General Information

Product Description

Vectra® MT1335 VF3001 (natural) is a glass/PTFE filled, tribologically-modified, easy flow LCP grade for injection molding.

Vectra® MT1335 VF3001 (natural) is a special grade developed for medical industry applications and complies with:

- Food Contact Substance Notification (FCN) No. 742 of the Food and Drug Administration (FDA) and is listed in the Drug Master File (DMF 8464) and the Device Master File (MAF 315)
- the corresponding EU and national registry regulatory requirements
- biocompatibility in tests corresponding to USP 23 Class VI/ISO 10993
- low residual monomers
- no animal products

Best High Current Arc Ignition (HAI) performance

Chemical abbreviation according to ISO 1043-1 : LCP

Inherently flame retardant

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Filler / Reinforcement	• Glass\PTFE		
Features	• Flame Retardant • Food Contact Acceptable	• Good Flow • No Animal Derived Components	
Uses	• Medical/Healthcare Applications		
Agency Ratings	• DMF 8464 • FDA FCN 742	• ISO 10993 • MAF 315	• USP XXIII, Class VI
RoHS Compliance	• Contact Manufacturer		
Processing Method	• Injection Molding		
Resin ID (ISO 1043)	• LCP		

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density	1.62	g/cm ³	ISO 1183
Molding Shrinkage			ISO 294-4
Across Flow	0.40	%	
Flow	0.10	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	1.60E+6	psi	ISO 527-2/1A
Tensile Stress (Break)	24800	psi	ISO 527-2/1A/5
Tensile Strain (Break)	3.3	%	ISO 527-2/1A/5
Flexural Modulus (73°F)	1.52E+6	psi	ISO 178
Flexural Stress (73°F)	29900	psi	ISO 178
Compressive Modulus	1.52E+6	psi	ISO 604
Compressive Stress (1% Strain)	11200	psi	ISO 604
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (73°F)	12	ft·lb/in ²	ISO 179/1eA

Vectra® MT1335

Celanese Corporation - Liquid Crystal Polymer

Impact	Nominal Value	Unit	Test Method
Charpy Unnotched Impact Strength (73°F)	18	ft-lb/in ²	ISO 179/1eU
Notched Izod Impact Strength (73°F)	8.1	ft-lb/in ²	ISO 180/1A
Unnotched Izod Impact Strength (73°F)	16	ft-lb/in ²	ISO 180/1U
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (M-Scale)	55		ISO 2039-2
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (66 psi, Unannealed)	482	°F	ISO 75-2/B
Heat Deflection Temperature (264 psi, Unannealed)	446	°F	ISO 75-2/A
Heat Deflection Temperature (1160 psi, Unannealed)	324	°F	ISO 75-2/C
Vicat Softening Temperature	295	°F	ISO 306/B50
Melting Temperature ²	536	°F	ISO 11357-3
CLTE - Flow	0.0	in/in/°F	ISO 11359-2
CLTE - Transverse	1.1E-5	in/in/°F	ISO 11359-2
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	> 1.0E+15	ohms	IEC 60093
Volume Resistivity	1.0E+15	ohms·cm	IEC 60093
Electric Strength	810	V/mil	IEC 60243-1
Relative Permittivity			IEC 60250
100 Hz	3.50		
1 MHz	3.10		
Dissipation Factor			IEC 60250
100 Hz	0.020		
1 MHz	0.016		
Arc Resistance	130	sec	Internal Method
Comparative Tracking Index	175	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating	V-0		UL 94

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	302	°F
Drying Time	4.0 to 6.0	hr
Suggested Max Moisture	0.010	%
Hopper Temperature	68 to 86	°F
Rear Temperature	518 to 536	°F
Middle Temperature	527 to 545	°F
Front Temperature	536 to 554	°F
Nozzle Temperature	554 to 572	°F
Processing (Melt) Temp	545 to 563	°F
Mold Temperature	176 to 248	°F
Injection Rate	Fast	
Back Pressure	< 435	psi

Injection Notes

Feeding zone temperature: 60 to 80°C
Zone4 temperature: 285 to 295°C
Hot runner temperature: 285 to 295°C

Vectra® MT1335

Celanese Corporation - Liquid Crystal Polymer

Notes

¹ Typical properties: these are not to be construed as specifications.

² 10°C/min
