



Vectra® S475

Celanese Corporation - Liquid Crystal Polymer

Sunday, November 3, 2019

General Information

Product Description

Super High Flow, High heat Resistance and Low Warp for Thin Parts. Chemical abbreviation according to ISO 1043-1 : LCP Inherently flame retardant UL-Listing V-0 in natural and black at 0.15mm thickness per UL 94 flame testing. Relative-Temperature-Index (RTI) according to UL 746B: electricals 130°C, mechanicals 130°C. UL = Underwriters Laboratories (USA)

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• Flame Retardant • High Flow	• High Heat Resistance • Low Warpage	
Uses	• Thin-walled Parts		
RoHS Compliance	• Contact Manufacturer		
Resin ID (ISO 1043)	• LCP		

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density	1.65	g/cm ³	ISO 1183
Molding Shrinkage			ISO 294-4
Across Flow	0.40	%	
Flow	0.0	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	1.78E+6	psi	ISO 527-2/1A
Tensile Stress (Break)	19600	psi	ISO 527-2/1A/5
Tensile Strain (Break)	1.8	%	ISO 527-2/1A/5
Flexural Modulus (73°F)	1.74E+6	psi	ISO 178
Flexural Stress (73°F)	26100	psi	ISO 178
Flexural Strain at Break	2.4	%	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (73°F)	2.4	ft·lb/in ²	ISO 179/1eA
Charpy Unnotched Impact Strength (73°F)	6.9	ft·lb/in ²	ISO 179/1eU
Notched Izod Impact Strength (73°F)	2.4	ft·lb/in ²	ISO 180/1A
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (264 psi, Unannealed)	581	°F	ISO 75-2/A
Heat Deflection Temperature (1160 psi, Unannealed)	415	°F	ISO 75-2/C
Melting Temperature ²	662	°F	ISO 11357-3
CLTE - Flow	5.6E-6	in/in/°F	ISO 11359-2
CLTE - Transverse	1.4E-5	in/in/°F	ISO 11359-2
Electrical	Nominal Value	Unit	Test Method
Relative Permittivity (1 MHz)	3.70		IEC 60250
Dissipation Factor (1 MHz)	8.0E-3		IEC 60250
Flammability	Nominal Value	Unit	Test Method
Flame Rating	V-0		UL 94

Vectra® S475

Celanese Corporation - Liquid Crystal Polymer

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	302	°F
Drying Time	6.0	hr
Suggested Max Moisture	0.010	%
Hopper Temperature	68 to 104	°F
Rear Temperature	626 to 662	°F
Middle Temperature	644 to 680	°F
Front Temperature	653 to 689	°F
Nozzle Temperature	671 to 698	°F
Processing (Melt) Temp	680 to 707	°F
Mold Temperature	176 to 248	°F
Injection Rate	Moderate	
Back Pressure	< 435	psi

Injection Notes

Feeding zone temperature: 60 to 80°C
Zone4 temperature: 355 to 370°C
Hot runner temperature: 355 to 370°C

Notes

¹ Typical properties: these are not to be construed as specifications.

² 10°C/min