



Vydyne® 21SPC

Ascend Performance Materials Operations LLC - Polyamide 66

Monday, November 4, 2019

General Information

Product Description

Vydyne 21SPC is a general-purpose PA66 resin. Available in natural color. It is designed principally for injection-molding fabrication. This resin offers a well balanced combination of engineering properties characterized by high strength; rigidity; good toughness; high melt point; good surface lubricity; abrasion resistance; and resistance to many chemicals, machine and motor oils, solvents and gasoline.

Vydyne 21SPC permits production of molded parts with good initial color plus good property and color retention when using regrind. This resin is recognized by Underwriters Laboratories and conforms to the requirements of many industrial, federal and military specifications for premium-quality, general-purpose PA66 resins.

Internally and externally lubricated for improved machine feed and exceptional mold release. Vydyne 21SPC is intended for use in high-productivity applications. In many applications, the molding cycle can be reduced because parts may be removed from the cavity at higher temperatures. In difficult molds where parts have a tendency to stick in the cavity, Vydyne 21SPC can reduce or eliminate the need for mold release sprays. Critical molded-part dimensions should be checked against specifications before implementing shorter molding cycles on a routine production basis.

Typical Applications/End Uses:

Vydyne 21SPC has been used in many molding applications such as terminal blocks, bearings, bushings, cams, electrical connectors and housings, electrical cable ties/tie straps and many other hardware and general industrial parts.

General

Material Status	• Commercial: Active		
Availability	• Asia Pacific	• Europe	• North America
Additive	• Lubricant		
Features	• Abrasion Resistant • Chemical Resistant • Fast Molding Cycle • Gasoline Resistant	• General Purpose • Good Mold Release • Good Toughness • High Rigidity	• High Strength • Lubricated • Oil Resistant • Solvent Resistant
Uses	• Bearings • Bushings • Cams	• Connectors • Electrical/Electronic Applications • Fasteners	• General Purpose • Housings • Industrial Applications
Agency Ratings	• ASTM D4066 PA0111 • ASTM D6779 PA0111 • EC 1935/2004	• EU 10/2011 • EU 2023/2006 • FDA 21 CFR 177.1500	• FED L-P-410A • MIL M-20693B • NSF STD-51
RoHS Compliance	• RoHS Compliant		
Automotive Specifications	• FORD WSK-M4D647-A	• GM GMP.PA66.005	• GM QK 002921
UL File Number	• E70062		
Appearance	• Natural Color		
Forms	• Pellets		
Processing Method	• Injection Molding		

ASTM & ISO Properties ¹

Physical	Dry	Conditioned	Unit	Test Method
Density	1.14	--	g/cm ³	ISO 1183
Molding Shrinkage				ISO 294-4
Across Flow : 73°F, 0.0787 in	1.7	--	%	
Flow : 73°F, 0.0787 in	1.8	--	%	
Water Absorption (24 hr, 73°F)	1.2	--	%	ISO 62

Vydyne® 21SPC

Ascend Performance Materials Operations LLC - Polyamide 66

Physical	Dry	Conditioned	Unit	Test Method
Water Absorption				ISO 62
Equilibrium, 73°F, 50% RH	2.4	--	%	
Outdoor Suitability (All Colors)	f2	--		UL 746C
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus (73°F)	450000	203000	psi	ISO 527-2
Tensile Stress (Yield, 73°F)	11900	7980	psi	ISO 527-2
Tensile Stress (Break, 73°F)	7980	6530	psi	ISO 527-2
Tensile Strain (Yield, 73°F)	5.0	25	%	ISO 527-2
Nominal Tensile Strain at Break				ISO 527-2
73°F	25	> 50	%	
Flexural Modulus (73°F)	421000	218000	psi	ISO 178
Flexural Strength (73°F)	11600	7250	psi	ISO 178
Poisson's Ratio	0.40	--		ISO 527
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179/1eA
-22°F	2.4	3.3	ft·lb/in ²	
73°F	2.9	9.5	ft·lb/in ²	
Charpy Unnotched Impact Strength				ISO 179/1eU
-22°F	No Break	No Break		
73°F	No Break	No Break		
Notched Izod Impact Strength				ISO 180
-22°F	2.4	3.3	ft·lb/in ²	
73°F	2.9	9.5	ft·lb/in ²	
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature				ISO 75-2/B
66 psi, Unannealed	392	--	°F	
Heat Deflection Temperature				ISO 75-2/A
264 psi, Unannealed	158	--	°F	
Melting Temperature	500	--	°F	ISO 11357-3
CLTE - Flow (73 to 131°F)	5.6E-5	--	in/in/°F	ISO 11359-2
CLTE - Transverse (73 to 131°F)	5.6E-5	--	in/in/°F	ISO 11359-2
RTI Elec				UL 746
0.016 in	266	--	°F	
0.028 in	266	--	°F	
0.06 in	266	--	°F	
0.12 in	266	--	°F	
RTI Imp				UL 746
0.016 in	167	--	°F	
0.028 in	167	--	°F	
0.06 in	167	--	°F	
0.12 in	167	--	°F	
RTI Str				UL 746
0.016 in	167	--	°F	
0.028 in	185	--	°F	
0.06 in	185	--	°F	
0.12 in	185	--	°F	
Electrical	Dry	Conditioned	Unit	Test Method
Volume Resistivity (0.0295 in)	1.0E+13	--	ohms·cm	IEC 60093

Vydyne® 21SPC

Ascend Performance Materials Operations LLC - Polyamide 66

Electrical	Dry	Conditioned	Unit	Test Method
Dielectric Strength (0.0394 in)	660	--	V/mil	IEC 60243
Arc Resistance (0.118 in)	PLC 5	--		ASTM D495
Comparative Tracking Index				IEC 60112
0.118 in	600	--	V	
High Amp Arc Ignition (HAI)				UL 746
0.016 in	PLC 1	--		
0.028 in	PLC 0	--		
0.06 in	PLC 0	--		
0.12 in	PLC 0	--		
High Voltage Arc Tracking Rate (HVTR)	PLC 0	--		UL 746
Hot-wire Ignition (HWI)				UL 746
0.016 in	PLC 4	--		
0.028 in	PLC 4	--		
0.06 in	PLC 3	--		
0.12 in	PLC 2	--		
Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating				UL 94
0.016 in	V-2	--		
0.028 in	V-2	--		
0.06 in	V-2	--		
0.12 in	V-2	--		
Glow Wire Flammability Index				IEC 60695-2-12
0.016 in	1760	--	°F	
0.028 in	1760	--	°F	
0.06 in	1760	--	°F	
0.12 in	1760	--	°F	
Glow Wire Ignition Temperature				IEC 60695-2-13
0.016 in	1520	--	°F	
0.028 in	1560	--	°F	
0.06 in	1560	--	°F	
0.12 in	1560	--	°F	
Oxygen Index	25	--	%	ISO 4589-2

Processing Information

Injection	Dry	Unit
Drying Temperature	< 158	°F
Drying Time	1.0 to 3.0	hr
Suggested Max Regrind	50	%
Rear Temperature	500 to 536	°F
Middle Temperature	518 to 545	°F
Front Temperature	536 to 554	°F
Nozzle Temperature	536 to 572	°F
Processing (Melt) Temp	545 to 572	°F
Mold Temperature	149 to 203	°F

Notes

¹ Typical properties: these are not to be construed as specifications.