



Vydyne® 22HSP NT

Ascend Performance Materials Operations LLC - Polyamide 66

Monday, November 4, 2019

General Information

Product Description

Vydyne 22HSP NT

General

Material Status	• Commercial: Active		
Availability	• Asia Pacific	• Europe	• North America
Additive	• Heat Stabilizer	• Lubricant	
Features	• Abrasion Resistant • Chemical Resistant • Fast Molding Cycle • Gasoline Resistant • General Purpose	• Good Mold Release • Good Toughness • Heat Stabilized • High Rigidity • High Strength	• Lubricated • Oil Resistant • Solvent Resistant
Uses	• Bearings • Bushings • Cams • Connectors	• Electrical/Electronic Applications • Fasteners • General Purpose • Housings	• Industrial Applications • Valves/Valve Parts • Washer
Agency Ratings	• ASTM D4066 PA0121 • ASTM D6779 PA0121	• FDA 21 CFR 177.1500 • FED L-P-410A	• MIL M-20693B
RoHS Compliance	• RoHS Compliant		
Automotive Specifications	• CHRYSLER MS-DB-41 CPN 1076 • CHRYSLER MS-DB-41 CPN 3490 • DELPHI M-5507	• FORD WSK-M4D648-A • GM GMP.PA66.018 • GM GMW16036P-PA66	• GM QK 002921 • HYUNDAI MS941-03 Type A-1 FRV2
UL File Number	• E70062		
Appearance	• Natural Color		
Forms	• Pellets		
Processing Method	• Injection Molding		

ASTM & ISO Properties ¹

Physical	Dry	Conditioned	Unit	Test Method
Density	1.14	--	g/cm ³	ISO 1183
Molding Shrinkage				ISO 294-4
Across Flow : 73°F, 0.0787 in	2.0	--	%	
Flow : 73°F, 0.0787 in	2.2	--	%	
Water Absorption (24 hr, 73°F)	1.2	--	%	ISO 62
Water Absorption				ISO 62
Equilibrium, 73°F, 50% RH	2.4	--	%	
Outdoor Suitability (Natural)	f1	--		UL 746C
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus (73°F)	450000	261000	psi	ISO 527-2
Tensile Stress (Yield, 73°F)	12300	7980	psi	ISO 527-2
Tensile Stress (Break, 73°F)	7980	5800	psi	ISO 527-2
Tensile Strain (Yield, 73°F)	5.0	20	%	ISO 527-2
Nominal Tensile Strain at Break				ISO 527-2
73°F	25	> 50	%	

UL and the UL logo are trademarks of UL LLC © 2019. All Rights Reserved.

The information presented here was acquired by UL from the producer of the product or material or original information provider. However, UL assumes no responsibility or liability for the accuracy of the information contained on this website and strongly encourages that upon final product or material selection information is validated with the manufacturer. This website provides links to other websites owned by third parties. The content of such third party sites is not within our control, and we cannot and will not take responsibility for the information or content.

Vydyne® 22HSP NT

Ascend Performance Materials Operations LLC - Polyamide 66

Mechanical	Dry	Conditioned	Unit	Test Method
Flexural Modulus (73°F)	421000	145000	psi	ISO 178
Flexural Strength (73°F)	13800	4350	psi	ISO 178
Poisson's Ratio	0.40	--		ISO 527
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179/1eA
-22°F	2.4	3.3	ft·lb/in ²	
73°F	2.9	9.5	ft·lb/in ²	
Charpy Unnotched Impact Strength				ISO 179/1eU
-22°F	No Break	No Break		
73°F	No Break	No Break		
Notched Izod Impact Strength				ISO 180
-22°F	2.4	3.3	ft·lb/in ²	
73°F	2.9	9.5	ft·lb/in ²	
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature				ISO 75-2/B
66 psi, Unannealed	392	--	°F	
Heat Deflection Temperature				ISO 75-2/A
264 psi, Unannealed	158	--	°F	
Melting Temperature	500	--	°F	ISO 11357-3
CLTE - Flow (73 to 131°F)	5.6E-5	--	in/in/°F	ISO 11359-2
CLTE - Transverse (73 to 131°F)	5.6E-5	--	in/in/°F	ISO 11359-2
RTI Elec				UL 746
0.028 in	284	--	°F	
0.06 in	284	--	°F	
0.12 in	284	--	°F	
RTI Imp				UL 746
0.028 in	203	--	°F	
0.06 in	230	--	°F	
0.12 in	230	--	°F	
RTI Str				UL 746
0.028 in	239	--	°F	
0.06 in	257	--	°F	
0.12 in	257	--	°F	
Electrical	Dry	Conditioned	Unit	Test Method
Volume Resistivity (0.0295 in)	1.0E+18	--	ohms·cm	IEC 60093
Dielectric Strength (0.0295 in)	500	--	V/mil	ASTM D149
Arc Resistance (0.118 in)	PLC 6	--		ASTM D495
Comparative Tracking Index				IEC 60112
0.118 in	400 to 599	--	V	
High Amp Arc Ignition (HAI)				UL 746
0.028 in	PLC 0	--		
0.06 in	PLC 0	--		
0.12 in	PLC 0	--		
High Voltage Arc Tracking Rate (HVTR)	PLC 0	--		UL 746
Hot-wire Ignition (HWI)				UL 746
0.028 in	PLC 4	--		
0.06 in	PLC 4	--		
0.12 in	PLC 4	--		

UL and the UL logo are trademarks of UL LLC © 2019. All Rights Reserved.

The information presented here was acquired by UL from the producer of the product or material or original information provider. However, UL assumes no responsibility or liability for the accuracy of the information contained on this website and strongly encourages that upon final product or material selection information is validated with the manufacturer. This website provides links to other websites owned by third parties. The content of such third party sites is not within our control, and we cannot and will not take responsibility for the information or content.

Vydyne® 22HSP NT

Ascend Performance Materials Operations LLC - Polyamide 66

Flammability	Dry	Conditioned	Unit	Test Method
Burning Rate				ISO 3795
0.0787 in, Self-Extinguishing	0.0	--	in/min	
Flame Rating				UL 94
0.028 in	V-2	--		
0.06 in	V-2	--		
0.12 in	V-2	--		
Glow Wire Flammability Index				IEC 60695-2-12
0.028 in	1520	--	°F	
0.06 in	1520	--	°F	
0.12 in	1760	--	°F	
Glow Wire Ignition Temperature				IEC 60695-2-13
0.028 in	1290	--	°F	
0.06 in	1290	--	°F	
0.12 in	1290	--	°F	
Oxygen Index	24	--	%	ISO 4589-2

Processing Information

Injection	Dry	Unit
Drying Temperature	< 158	°F
Drying Time	1.0 to 3.0	hr
Suggested Max Regrind	50	%
Rear Temperature	500 to 536	°F
Middle Temperature	518 to 545	°F
Front Temperature	536 to 554	°F
Nozzle Temperature	536 to 572	°F
Processing (Melt) Temp	545 to 572	°F
Mold Temperature	149 to 203	°F

Notes

¹ Typical properties: these are not to be construed as specifications.