



## Vydyne® 47H NT0688

Ascend Performance Materials Operations LLC - Polyamide 66

Monday, November 4, 2019

### General Information

#### Product Description

47H NT0688 is a high-performance, medium-impact-modified, heat-stabilized grade of PA66 resin.

#### General

|                           |                                                                                                                    |                                                                                                                               |                                                                       |
|---------------------------|--------------------------------------------------------------------------------------------------------------------|-------------------------------------------------------------------------------------------------------------------------------|-----------------------------------------------------------------------|
| Material Status           | • Commercial: Active                                                                                               |                                                                                                                               |                                                                       |
| Availability              | • Asia Pacific                                                                                                     | • Europe                                                                                                                      | • North America                                                       |
| Additive                  | • Heat Stabilizer                                                                                                  | • Impact Modifier                                                                                                             |                                                                       |
| Features                  | • Abrasion Resistant<br>• Chemical Resistant<br>• Gasoline Resistant<br>• General Purpose<br>• Good Processability | • Good Toughness<br>• Heat Stabilized<br>• High Impact Resistance<br>• Impact Modified<br>• Low Temperature Impact Resistance | • Low Temperature Toughness<br>• Oil Resistant<br>• Solvent Resistant |
| Uses                      | • Automotive Applications<br>• Connectors<br>• Consumer Applications                                               | • Electrical/Electronic Applications<br>• Fasteners<br>• Gears                                                                | • Industrial Applications                                             |
| Agency Ratings            | • ASTM D4066 PA0161                                                                                                | • ASTM D6779 PA0161                                                                                                           |                                                                       |
| Automotive Specifications | • CHRYSLER MS-DB-41 CPN 2055<br>• FORD ESB-M4D178-A2<br>• FORD WSK-M4D706-A                                        | • FORD WSS-M4D706-B1<br>• GM GMP.PA66.015<br>• GM GMW16447P-PA66-T2                                                           | • HYUNDAI MS941-03 Type A-1                                           |
| Appearance                | • Natural Color                                                                                                    |                                                                                                                               |                                                                       |
| Forms                     | • Pellets                                                                                                          |                                                                                                                               |                                                                       |
| Processing Method         | • Injection Molding                                                                                                |                                                                                                                               |                                                                       |

### ASTM & ISO Properties <sup>1</sup>

| Physical                       | Dry    | Conditioned | Unit              | Test Method |
|--------------------------------|--------|-------------|-------------------|-------------|
| Density                        | 1.10   | --          | g/cm <sup>3</sup> | ISO 1183    |
| Molding Shrinkage              |        |             |                   | ISO 294-4   |
| Across Flow : 73°F, 0.0787 in  | 1.6    | --          | %                 |             |
| Flow : 73°F, 0.0787 in         | 1.8    | --          | %                 |             |
| Water Absorption (24 hr, 73°F) | 1.2    | --          | %                 | ISO 62      |
| Water Absorption               |        |             |                   | ISO 62      |
| Equilibrium, 73°F, 50% RH      | 2.3    | --          | %                 |             |
| Mechanical                     | Dry    | Conditioned | Unit              | Test Method |
| Tensile Modulus (73°F)         | 403000 | 252000      | psi               | ISO 527-2   |
| Tensile Stress (Yield, 73°F)   | 8700   | 6530        | psi               | ISO 527-2   |
| Tensile Stress (Break, 73°F)   | 7540   | 5800        | psi               | ISO 527-2   |
| Tensile Strain (Break, 73°F)   | 22     | 60          | %                 | ISO 527-2   |
| Flexural Modulus (73°F)        | 334000 | 113000      | psi               | ISO 178     |
| Flexural Strength (73°F)       | 10200  | 3480        | psi               | ISO 178     |

# Vydyne® 47H NT0688

## Ascend Performance Materials Operations LLC - Polyamide 66

| Impact                                     | Dry      | Conditioned | Unit                  | Test Method |
|--------------------------------------------|----------|-------------|-----------------------|-------------|
| Charpy Notched Impact Strength             |          |             |                       | ISO 179/1eA |
| -40°F                                      | 5.2      | 8.6         | ft·lb/in <sup>2</sup> |             |
| -22°F                                      | 8.1      | 11          | ft·lb/in <sup>2</sup> |             |
| 73°F                                       | 9.0      | 30          | ft·lb/in <sup>2</sup> |             |
| Charpy Unnotched Impact Strength           |          |             |                       | ISO 179/1eU |
| -22°F                                      | No Break | No Break    |                       |             |
| 73°F                                       | No Break | No Break    |                       |             |
| Notched Izod Impact Strength               |          |             |                       | ISO 180     |
| -40°F                                      | 5.7      | 8.6         | ft·lb/in <sup>2</sup> |             |
| -22°F                                      | 7.6      | 11          | ft·lb/in <sup>2</sup> |             |
| 73°F                                       | 8.6      | 21          | ft·lb/in <sup>2</sup> |             |
| Thermal                                    | Dry      | Conditioned | Unit                  | Test Method |
| Heat Deflection Temperature                |          |             |                       | ISO 75-2/B  |
| 66 psi, Unannealed                         | 365      | --          | °F                    |             |
| Heat Deflection Temperature                |          |             |                       | ISO 75-2/A  |
| 264 psi, Unannealed                        | 145      | --          | °F                    |             |
| Melting Temperature                        | 500      | --          | °F                    | ISO 11357-3 |
| CLTE - Flow (73 to 131°F, 0.0787 in)       | 6.2E-5   | --          | in/in/°F              | ISO 11359-2 |
| CLTE - Transverse (73 to 131°F, 0.0787 in) | 7.6E-5   | --          | in/in/°F              | ISO 11359-2 |
| RTI Elec                                   |          |             |                       | UL 746      |
| 0.030 in                                   | 266      | --          | °F                    |             |
| 0.06 in                                    | 266      | --          | °F                    |             |
| 0.12 in                                    | 266      | --          | °F                    |             |
| RTI Imp                                    |          |             |                       | UL 746      |
| 0.030 in                                   | 167      | --          | °F                    |             |
| 0.06 in                                    | 167      | --          | °F                    |             |
| 0.12 in                                    | 167      | --          | °F                    |             |
| RTI Str                                    |          |             |                       | UL 746      |
| 0.030 in                                   | 239      | --          | °F                    |             |
| 0.06 in                                    | 239      | --          | °F                    |             |
| 0.12 in                                    | 239      | --          | °F                    |             |
| Electrical                                 | Dry      | Conditioned | Unit                  | Test Method |
| Volume Resistivity (0.0295 in)             | 1.0E+11  | --          | ohms·cm               | IEC 60093   |
| Dielectric Strength (0.0394 in)            | 300      | --          | V/mil                 | IEC 60243   |
| Arc Resistance                             | PLC 6    | --          |                       | ASTM D495   |
| Comparative Tracking Index                 |          |             |                       | IEC 60112   |
| 0.118 in                                   | 525      | --          | V                     |             |
| High Amp Arc Ignition (HAI)                |          |             |                       | UL 746      |
| 0.030 in                                   | PLC 0    | --          |                       |             |
| 0.06 in                                    | PLC 0    | --          |                       |             |
| 0.12 in                                    | PLC 0    | --          |                       |             |
| High Voltage Arc Tracking Rate (HVTR)      | PLC 2    | --          |                       | UL 746      |
| Hot-wire Ignition (HWI)                    |          |             |                       | UL 746      |
| 0.030 in                                   | PLC 4    | --          |                       |             |
| 0.06 in                                    | PLC 4    | --          |                       |             |
| 0.12 in                                    | PLC 3    | --          |                       |             |

# Vydyne® 47H NT0688

## Ascend Performance Materials Operations LLC - Polyamide 66

| Flammability                                | Dry  | Conditioned | Unit | Test Method    |
|---------------------------------------------|------|-------------|------|----------------|
| Flame Rating                                |      |             |      | UL 94          |
| 0.030 in                                    | HB   | --          |      |                |
| 0.06 in                                     | HB   | --          |      |                |
| 0.12 in                                     | HB   | --          |      |                |
| Glow Wire Flammability Index                |      |             |      | IEC 60695-2-12 |
| 0.030 in                                    | 1290 | --          | °F   |                |
| 0.06 in                                     | 1430 | --          | °F   |                |
| 0.12 in                                     | 1290 | --          | °F   |                |
| Glow Wire Ignition Temperature              |      |             |      | IEC 60695-2-13 |
| 0.030 in                                    | 1340 | --          | °F   |                |
| 0.06 in                                     | 1470 | --          | °F   |                |
| 0.12 in                                     | 1340 | --          | °F   |                |
| Additional Information                      | Dry  | Conditioned | Unit | Test Method    |
| Automotive Materials - (thickness d = 1 mm) | +    | --          |      | FMVSS 302      |

### Processing Information

| Injection              | Dry        | Unit |
|------------------------|------------|------|
| Drying Temperature     | 176        | °F   |
| Drying Time            | 4.0        | hr   |
| Suggested Max Regrind  | 25         | %    |
| Rear Temperature       | 536 to 590 | °F   |
| Middle Temperature     | 536 to 590 | °F   |
| Front Temperature      | 536 to 590 | °F   |
| Nozzle Temperature     | 536 to 590 | °F   |
| Processing (Melt) Temp | 545 to 581 | °F   |
| Mold Temperature       | 149 to 203 | °F   |

### Notes

<sup>1</sup> Typical properties: these are not to be construed as specifications.