



Vydyne® ECO315

Ascend Performance Materials Operations LLC - Polyamide 66/6 Copolymer

Monday, November 4, 2019

General Information

Product Description

Vydyne ECO315 is a non-halogenated, unfilled, flame-retardant PA66/6 copolymer with excellent toughness and ductility. It is lubricated for machine feed and easy mold release and has an Underwriters Laboratories UL 94 flammability classification of V-0 at 0.4 mm (0.016") thick.

General

Material Status	• Commercial: Active		
Availability	• Asia Pacific	• Europe	• North America
Additive	• Flame Retardant	• Lubricant	
Features	• Crack Resistant • Ductile • Flame Retardant	• Good Mold Release • Good Toughness • Halogen Free	• High Elongation • Low Density • Lubricated
Uses	• Appliances • Automotive Electronics • Bobbins • Connectors • Electrical Housing	• Electrical Parts • Electrical/Electronic Applications • Fasteners • Industrial Applications • Lighting Applications	• Living Hinges • Printed Circuit Boards • Switches
UL File Number	• E70062		
Appearance	• Natural Color		
Forms	• Pellets		
Processing Method	• Injection Molding		

ASTM & ISO Properties ¹

Physical	Dry	Conditioned	Unit	Test Method
Density	1.16	--	g/cm ³	ISO 1183
Molding Shrinkage				ISO 294-4
Across Flow : 73°F, 0.0787 in	1.4	--	%	
Flow : 73°F, 0.0787 in	1.2	--	%	
Water Absorption (24 hr, 73°F)	0.80	--	%	ISO 62
Water Absorption				ISO 62
Equilibrium, 73°F, 50% RH	2.3	--	%	
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus (73°F)	471000	174000	psi	ISO 527-2
Tensile Stress (Yield, 73°F)	10900	6090	psi	ISO 527-2
Tensile Strain (Yield, 73°F)	3.5	23	%	ISO 527-2
Tensile Strain (Break, 73°F)	22	140	%	ISO 527-2
Flexural Modulus (73°F)	464000	226000	psi	ISO 178
Flexural Strength (73°F)	13300	6530	psi	ISO 178
Poisson's Ratio	0.40	--		ISO 527-2
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179/1eA
-22°F	2.6	--	ft·lb/in ²	
73°F	2.6	--	ft·lb/in ²	
Charpy Unnotched Impact Strength				ISO 179/1eU
-22°F	No Break	--		
73°F	No Break	--		

Vydyne® ECO315

Ascend Performance Materials Operations LLC - Polyamide 66/6 Copolymer

Impact	Dry	Conditioned	Unit	Test Method
Notched Izod Impact Strength 73°F	2.9	--	ft·lb/in ²	ISO 180
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature 66 psi, Unannealed	437	--	°F	ISO 75-2/B
Heat Deflection Temperature 264 psi, Unannealed	149	--	°F	ISO 75-2/A
Melting Temperature	471	--	°F	ISO 11357-3
CLTE - Flow (73 to 131°F, 0.0787 in)	6.1E-5	--	in/in/°F	ISO 11359-2
CLTE - Transverse (73 to 131°F, 0.0787 in)	6.1E-5	--	in/in/°F	ISO 11359-2
RTI Elec				UL 746
0.016 in	266	--	°F	
0.030 in	266	--	°F	
0.06 in	266	--	°F	
0.12 in	266	--	°F	
RTI Imp				UL 746
0.016 in	149	--	°F	
0.030 in	149	--	°F	
0.06 in	185	--	°F	
0.12 in	185	--	°F	
RTI Str				UL 746
0.016 in	212	--	°F	
0.030 in	212	--	°F	
0.06 in	212	--	°F	
0.12 in	230	--	°F	
Electrical	Dry	Conditioned	Unit	Test Method
Volume Resistivity (0.0295 in)	1.0E+11	--	ohms·cm	IEC 60093
Dielectric Strength (0.0394 in)	330	--	V/mil	IEC 60243
Arc Resistance (0.118 in)	PLC 5	--		ASTM D495
Comparative Tracking Index 0.118 in	600	--	V	IEC 60112
High Amp Arc Ignition (HAI)				UL 746
0.016 in	PLC 0	--		
0.030 in	PLC 0	--		
0.06 in	PLC 0	--		
0.12 in	PLC 0	--		
High Voltage Arc Tracking Rate (HVTR)	PLC 1	--		UL 746
Hot-wire Ignition (HWI)				UL 746
0.016 in	PLC 4	--		
0.030 in	PLC 4	--		
0.06 in	PLC 4	--		
0.12 in	PLC 3	--		
Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating				UL 94
0.016 in	V-0	--		
0.030 in	V-0	--		
0.06 in	V-0	--		
0.12 in	V-0	--		

UL and the UL logo are trademarks of UL LLC © 2019. All Rights Reserved.

The information presented here was acquired by UL from the producer of the product or material or original information provider. However, UL assumes no responsibility or liability for the accuracy of the information contained on this website and strongly encourages that upon final product or material selection information is validated with the manufacturer. This website provides links to other websites owned by third parties. The content of such third party sites is not within our control, and we cannot and will not take responsibility for the information or content.

Vydyne® ECO315

Ascend Performance Materials Operations LLC - Polyamide 66/6 Copolymer

Flammability	Dry	Conditioned	Unit	Test Method
Glow Wire Flammability Index				IEC 60695-2-12
0.016 in	1760	--	°F	
0.030 in	1760	--	°F	
0.06 in	1760	--	°F	
0.12 in	1760	--	°F	
Glow Wire Ignition Temperature				IEC 60695-2-13
0.016 in	1610	--	°F	
0.030 in	1610	--	°F	
0.06 in	1430	--	°F	
0.12 in	1340	--	°F	
Oxygen Index	29	--	%	ISO 4589-2

Processing Information

Injection	Dry	Unit
Drying Temperature	176	°F
Drying Time	4.0	hr
Suggested Max Regrind	50	%
Rear Temperature	464 to 518	°F
Middle Temperature	464 to 518	°F
Front Temperature	464 to 518	°F
Nozzle Temperature	464 to 518	°F
Processing (Melt) Temp	482 to 518	°F
Mold Temperature	149 to 203	°F

Notes

¹ Typical properties: these are not to be construed as specifications.