



Vydyne® ECO366H NT0708

Ascend Performance Materials Operations LLC - Polyamide 66

Monday, November 4, 2019

General Information

Product Description

Vydyne ECO366H NT0708 is an unfilled, PA66 homopolymer utilizing a non-halogen flame retardant, designed with superior flow properties to assist in filling thin-walled, intricate parts. It is stabilized to provide heat stability up to 170°C for 1,000 hours. ECO366H NT0708 is also lubricated for machine feed and easy mold release and has an Underwriters Laboratories UL 94 flammability classification of V-0 at 0.2mm (0.008") thick.

General

Material Status	• Commercial: Active		
Availability	• Asia Pacific	• Europe	• North America
Additive	• Flame Retardant	• Heat Stabilizer	• Lubricant
Features	• Chemical Resistant	• Good Electrical Properties	• Heat Stabilized
	• Corrosion Resistant	• Good Mold Release	• Ignition Resistant
	• Flame Retardant	• Heat Aging Resistant	• Lubricated
Uses	• Appliances	• Electrical Parts	
	• Automotive Electronics	• Electrical/Electronic Applications	• Living Hinges
	• Bobbins	• Fasteners	• Printed Circuit Boards
	• Connectors	• Industrial Applications	• Switches
	• Electrical Housing	• Lighting Applications	
RoHS Compliance	• RoHS Compliant		
UL File Number	• E70062		
Appearance	• Natural Color		
Forms	• Pellets		
Processing Method	• Injection Molding		

ASTM & ISO Properties ¹

Physical	Dry	Conditioned	Unit	Test Method
Density	1.17	--	g/cm ³	ISO 1183
Molding Shrinkage				ISO 294-4
Across Flow : 73°F, 0.0787 in	1.2	--	%	
Flow : 73°F, 0.0787 in	0.90	--	%	
Water Absorption (24 hr, 73°F)	0.80	--	%	ISO 62
Water Absorption				ISO 62
Equilibrium, 73°F, 50% RH	2.3	--	%	
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Stress (Yield, 73°F)	12000	8410	psi	ISO 527-2
Tensile Strain (Break, 73°F)	6.0	7.0	%	ISO 527-2
Flexural Modulus (73°F)	566000	196000	psi	ISO 178
Flexural Strength (73°F)	15500	5660	psi	ISO 178
Poisson's Ratio	0.40	--		ISO 527-2
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179/1eA
-22°F	1.8	--	ft·lb/in ²	
73°F	1.6	--	ft·lb/in ²	
Charpy Unnotched Impact Strength				ISO 179/1eU
-22°F	37	--	ft·lb/in ²	
73°F	36	--	ft·lb/in ²	

UL and the UL logo are trademarks of UL LLC © 2019. All Rights Reserved.

The information presented here was acquired by UL from the producer of the product or material or original information provider. However, UL assumes no responsibility or liability for the accuracy of the information contained on this website and strongly encourages that upon final product or material selection information is validated with the manufacturer. This website provides links to other websites owned by third parties. The content of such third party sites is not within our control, and we cannot and will not take responsibility for the information or content.

Vydyne® ECO366H NT0708

Ascend Performance Materials Operations LLC - Polyamide 66

Impact	Dry	Conditioned	Unit	Test Method
Notched Izod Impact Strength 73°F	2.9	--	ft·lb/in ²	ISO 180
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature 66 psi, Unannealed	464	--	°F	ISO 75-2/B
Heat Deflection Temperature 264 psi, Unannealed	167	--	°F	ISO 75-2/A
Melting Temperature	509	--	°F	ISO 11357-3
RTI Elec				UL 746
0.016 in	302	--	°F	
0.030 in	302	--	°F	
0.06 in	302	--	°F	
0.12 in	302	--	°F	
RTI Imp				UL 746
0.016 in	230	--	°F	
0.030 in	230	--	°F	
0.06 in	230	--	°F	
0.12 in	230	--	°F	
RTI Str				UL 746
0.016 in	266	--	°F	
0.030 in	266	--	°F	
0.06 in	266	--	°F	
0.12 in	266	--	°F	
Electrical	Dry	Conditioned	Unit	Test Method
Volume Resistivity (0.0295 in)	1.0E+19	--	ohms·cm	IEC 60093
Dielectric Strength (0.0394 in)	510	--	V/mil	IEC 60243
Arc Resistance (0.118 in)	PLC 5	--		ASTM D495
Comparative Tracking Index 0.118 in	600	--	V	IEC 60112
High Amp Arc Ignition (HAI)				UL 746
0.016 in	PLC 0	--		
0.030 in	PLC 0	--		
0.06 in	PLC 0	--		
0.12 in	PLC 0	--		
High Voltage Arc Tracking Rate (HVTR)	PLC 0	--		UL 746
Hot-wire Ignition (HWI)				UL 746
0.016 in	PLC 4	--		
0.030 in	PLC 3	--		
0.06 in	PLC 3	--		
0.12 in	PLC 1	--		
Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating				UL 94
0.0079 in	V-0	--		
0.016 in	V-0	--		
0.030 in	V-0	--		
0.06 in	V-0	--		
0.12 in	V-0	--		

Vydyne® ECO366H NT0708

Ascend Performance Materials Operations LLC - Polyamide 66

Flammability	Dry	Conditioned	Unit	Test Method
Glow Wire Flammability Index				IEC 60695-2-12
0.016 in	1760	--	°F	
0.030 in	1760	--	°F	
0.06 in	1760	--	°F	
0.12 in	1760	--	°F	
Glow Wire Ignition Temperature				IEC 60695-2-13
0.016 in	1760	--	°F	
0.030 in	1760	--	°F	
0.06 in	1470	--	°F	
0.12 in	1430	--	°F	
Oxygen Index	35	--	%	ISO 4589-2

Processing Information

Injection	Dry	Unit
Drying Temperature	176	°F
Drying Time	4.0	hr
Suggested Max Regrind	50	%
Rear Temperature	500 to 554	°F
Middle Temperature	500 to 554	°F
Front Temperature	500 to 554	°F
Nozzle Temperature	500 to 554	°F
Processing (Melt) Temp	518 to 545	°F
Mold Temperature	149 to 203	°F

Notes

¹ Typical properties: these are not to be construed as specifications.