



Vydyne® R530 NAT

Ascend Performance Materials Operations LLC - Polyamide 66

Monday, November 4, 2019

General Information

Product Description

Vydyne R530 NAT is general-purpose, injection-molding grade, 30% glass-fiber reinforced PA66 resin. Available in natural, it is lubricated for good machine feed, flow and mold release.

General

Material Status	• Commercial: Active		
Availability	• Asia Pacific	• Europe	• North America
Filler / Reinforcement	• Glass Fiber, 30% Filler by Weight		
Additive	• Lubricant		
Features	• Antifreeze Resistant • Chemical Resistant • Fatigue Resistant	• Gasoline Resistant • Good Flow • Heat Stabilized	• Hydrolysis Resistant • Lubricated • Solvent Resistant
Uses	• Automotive Under the Hood		
Agency Ratings	• ASTM D4066 PA011G30 • ASTM D6779 PA011G30	• EC 1935/2004 • EU 10/2011	• EU 2023/2006 • FDA 21 CFR 177.1500
UL File Number	• E70062		
Appearance	• Natural Color		
Forms	• Pellets		
Processing Method	• Injection Molding		

ASTM & ISO Properties ¹

Physical	Dry	Conditioned	Unit	Test Method
Density	1.37	--	g/cm ³	ISO 1183
Molding Shrinkage				ISO 294-4
Across Flow : 73°F, 0.0787 in	0.90	--	%	
Flow : 73°F, 0.0787 in	0.40	--	%	
Water Absorption (24 hr, 73°F)	0.90	--	%	ISO 62
Water Absorption				ISO 62
Equilibrium, 73°F, 50% RH	1.9	--	%	
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus (73°F)	1.45E+6	1.07E+6	psi	ISO 527-2
Tensile Stress (Break, 73°F)	28300	19600	psi	ISO 527-2
Tensile Strain (Break, 73°F)	3.0	5.0	%	ISO 527-2
Flexural Modulus (73°F)	1.39E+6	870000	psi	ISO 178
Flexural Stress (73°F)	39200	27600	psi	ISO 178
Poisson's Ratio (73°F)	0.40	--		ISO 527
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179
-22°F	4.9	5.2	ft·lb/in ²	
73°F	5.3	6.2	ft·lb/in ²	
Charpy Unnotched Impact Strength				ISO 179
-22°F	31	38	ft·lb/in ²	
73°F	36	40	ft·lb/in ²	

Vydyne® R530 NAT

Ascend Performance Materials Operations LLC - Polyamide 66

Impact	Dry	Conditioned	Unit	Test Method
Notched Izod Impact Strength				ISO 180
-22°F	4.8	5.2	ft·lb/in ²	
73°F	5.7	6.2	ft·lb/in ²	
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature				ISO 75-2/B
66 psi, Unannealed	500	--	°F	
Heat Deflection Temperature				ISO 75-2/A
264 psi, Unannealed	482	--	°F	
Melting Temperature	500	--	°F	ISO 11357-3
CLTE - Flow (73 to 131°F, 0.0787 in)	1.2E-5	--	in/in/°F	ISO 11359-2
CLTE - Transverse (73 to 131°F, 0.0787 in)	5.9E-5	--	in/in/°F	ISO 11359-2
RTI Elec				UL 746
0.030 in	248	--	°F	
0.06 in	248	--	°F	
0.12 in	248	--	°F	
RTI Imp				UL 746
0.030 in	185	--	°F	
0.06 in	185	--	°F	
0.12 in	221	--	°F	
RTI Str				UL 746
0.030 in	239	--	°F	
0.06 in	248	--	°F	
0.12 in	248	--	°F	
Electrical	Dry	Conditioned	Unit	Test Method
Volume Resistivity (0.118 in)	1.0E+14	--	ohms·cm	IEC 60093
Dielectric Strength (0.0394 in)	610	--	V/mil	IEC 60243
Arc Resistance (0.118 in)	PLC 5	--		ASTM D495
Comparative Tracking Index				IEC 60112
0.118 in	600	--	V	
High Amp Arc Ignition (HAI)				UL 746
0.030 in	PLC 0	--		
0.06 in	PLC 0	--		
0.12 in	PLC 0	--		
High Voltage Arc Tracking Rate (HVTR)	PLC 1	--		UL 746
Hot-wire Ignition (HWI)				UL 746
0.030 in	PLC 4	--		
0.06 in	PLC 4	--		
0.12 in	PLC 4	--		
Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating				UL 94
0.030 in	HB	--		
0.06 in	HB	--		
0.12 in	HB	--		

Vydyne® R530 NAT

Ascend Performance Materials Operations LLC - Polyamide 66

Processing Information

Injection	Dry	Unit
Drying Temperature	176	°F
Drying Time	4.0	hr
Suggested Max Regrind	25	%
Rear Temperature	536 to 590	°F
Middle Temperature	536 to 590	°F
Front Temperature	536 to 590	°F
Nozzle Temperature	536 to 590	°F
Processing (Melt) Temp	545 to 581	°F
Mold Temperature	149 to 203	°F

Notes

¹ Typical properties: these are not to be construed as specifications.