

Vydyne® R860 BK02

Ascend Performance Materials Operations LLC - Polyamide 66

Monday, November 4, 2019

General Information

Product Description

Vydyne R860 BK02 is general-purpose, glass-fiber and mineral-reinforced PA66 resin. Available in black, this product is also lubricated for improved flow and offers superior surface appearance.

Glass fiber and mineral-reinforced Vydyne resins provide higher heat distortion temperature, resistance to creep and better dimensional stability when compared with unreinforced PA66. These products have good chemical resistance to a broad range of chemicals including gasoline, hydraulic fluids and most solvents.

Typical Applications/End Uses:

Vydyne R860 BK02 can be successfully used in a wide range of injection-molding engineering applications. Typical parts include automotive clips, radiator shrouds, fans and mirror brackets; electrical connectors, housings and bobbins; and industrial applications such as gears, bearing shells, covers and housings.

General			
Material Status	Commercial: Active		
Availability	Asia Pacific	• Europe	North America
Filler / Reinforcement	Glass Fiber	Mineral	
Additive	Lubricant		
Features	 Good Mold Release High Rigidity	 High Strength High Tensile Strength	LubricatedOutstanding Surface Finish
Uses	Automotive Under the HoodBearings	ConnectorsHousings	
Agency Ratings	 ASTM D4066 PA114R35 	• ASTM D6779 PA084R35	
Automotive Specifications	 BOSCH VDA EMPB CHRYSLER MS-DB-41 CPN 2554 	FORD ESB-M4D353-A7GM GMP.PA66.003	GM GMP.PA66.042R HYUNDAI MS211-47 Type (
UL File Number	• E70062		
Appearance	Black		
Forms	• Pellets		
Processing Method	Injection Molding		

ASTM & ISO Properties 1						
Physical	Dry	Conditioned	Unit	Test Method		
Density	1.47		g/cm³	ISO 1183		
Molding Shrinkage				ISO 294-4		
Across Flow: 73°F, 0.0787 in	0.80		%			
Flow: 73°F, 0.0787 in	0.25		%			
Water Absorption (24 hr, 73°F)	0.60		%	ISO 62		
Water Absorption				ISO 62		
Equilibrium, 73°F, 50% RH	2.0		%			
Mechanical	Dry	Conditioned	Unit	Test Method		
Tensile Modulus (73°F)	1.45E+6	856000	psi	ISO 527-2		
Tensile Stress (Break, 73°F)	17400	13100	psi	ISO 527-2		
Tensile Strain (Break, 73°F)	2.5	2.8	%	ISO 527-2		
Flexural Modulus (73°F)	1.31E+6	653000	psi	ISO 178		
Flexural Stress (73°F)	27600	14100	psi	ISO 178		



Vydyne® R860 BK02

Ascend Performance Materials Operations LLC - Polyamide 66

Mechanical	Dry	Conditioned	Unit	Test Method
Poisson's Ratio	0.40			ISO 527-2
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179
-22°F	1.8	2.9	ft·lb/in²	
73°F	2.1	4.8	ft·lb/in²	
Charpy Unnotched Impact Strength				ISO 179
-22°F	20	29	ft·lb/in²	
73°F	23	27	ft·lb/in²	
Notched Izod Impact Strength				ISO 180
-22°F	2.2	3.1	ft·lb/in²	
73°F	2.7	4.8	ft·lb/in²	
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature				ISO 75-2/B
66 psi, Unannealed	446		°F	
Heat Deflection Temperature				ISO 75-2/A
264 psi, Unannealed	419		°F	
Melting Temperature	491		°F	ISO 11357-3
CLTE - Flow (73 to 131°F, 0.0787 in)	1.3E-4		in/in/°F	ISO 11359-2
CLTE - Transverse (73 to 131°F, 0.0787 in)	3.8E-4	-	in/in/°F	ISO 11359-2
	Processing Info	rmation		
njection		Dry Unit		
Drying Temperature		176 °F		
Drying Time		4.0 hr		
Suggested Max Regrind		25 %		
Rear Temperature		536 to 590 °F		
Middle Temperature		536 to 590 °F		
Front Temperature		536 to 590 °F		
Nozzle Temperature		536 to 590 °F		
Processing (Melt) Temp		545 to 581 °F		
Mold Temperature		149 to 203 °F		

Notes

¹ Typical properties: these are not to be construed as specifications.