



Zenite® 5130L

Celanese Corporation - Liquid Crystal Polymer

Sunday, November 3, 2019

General Information

Product Description

Zenite 5130L is a 30% glass-reinforced LCP resin with improved toughness

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Filler / Reinforcement	• Glass Fiber, 30% Filler by Weight		
Features	• Good Toughness		
RoHS Compliance	• Contact Manufacturer		

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density	1.63	g/cm ³	ISO 1183
Molding Shrinkage			ISO 294-4
Across Flow	0.70	%	
Flow	0.10	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	1.45E+6	psi	ISO 527-2/1A
Tensile Stress (Break)	21000	psi	ISO 527-2/1A/5
Tensile Strain (Break)	3.5	%	ISO 527-2/1A/5
Flexural Modulus (73°F)	1.60E+6	psi	ISO 178
Flexural Stress (73°F)	24700	psi	ISO 178
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (264 psi, Unannealed)	527	°F	ISO 75-2/A
Melting Temperature ²	608	°F	ISO 11357-3
Electrical	Nominal Value	Unit	Test Method
Relative Permittivity (1 MHz)	3.30		IEC 60250
Dissipation Factor (1 MHz)	8.0E-3		IEC 60250
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.031 in)	V-0		UL 94

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	302	°F
Drying Time	3.0	hr
Suggested Max Moisture	0.010	%
Hopper Temperature	68 to 86	°F
Rear Temperature	608 to 626	°F
Middle Temperature	635 to 653	°F
Front Temperature	635 to 653	°F
Nozzle Temperature	635 to 653	°F
Processing (Melt) Temp	617 to 653	°F
Mold Temperature	176 to 248	°F

Zenite® 5130L

Celanese Corporation - Liquid Crystal Polymer

Injection	Nominal Value	Unit
Back Pressure	< 435	psi

Injection Notes

Feeding zone temperature: 40 to 60°C
Zone4 temperature: 335 to 345°C

Notes

¹ Typical properties: these are not to be construed as specifications.

² 10°C/min