



Zenite® SEA20N

Celanese Corporation - Liquid Crystal Polymer

Sunday, November 3, 2019

General Information

Product Description

ZENITE® SEA20N is a 40% mineral filled grade. It offers excellent surface appearance, low warpage, and excellent dimensional stability. Application for this grade is compact camera module, and other thin, small electronic parts

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Filler / Reinforcement	• Mineral, 40% Filler by Weight		
Features	• Good Dimensional Stability	• Good Surface Finish	• Low Warpage
Uses	• Camera Applications	• Electrical/Electronic Applications • Thin-walled Parts	

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density	1.77	g/cm ³	ISO 1183
Molding Shrinkage			ISO 294-4
Across Flow	0.80	%	
Flow	0.20	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	1.45E+6	psi	ISO 527-2/1A
Tensile Stress (Break)	15200	psi	ISO 527-2/1A/5
Tensile Strain (Break)	4.2	%	ISO 527-2/1A/5
Flexural Modulus (73°F)	1.45E+6	psi	ISO 178
Flexural Stress (73°F)	18300	psi	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (73°F)	2.1	ft·lb/in ²	ISO 179/1eA
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (264 psi, Unannealed)	428	°F	ISO 75-2/A
Melting Temperature ²	626	°F	ISO 11357-3

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	302	°F
Drying Time	6.0	hr
Rear Temperature	590 to 608	°F
Middle Temperature	608 to 626	°F
Front Temperature	626 to 662	°F
Nozzle Temperature	626 to 644	°F
Processing (Melt) Temp	635 to 653	°F
Mold Temperature	176 to 284	°F
Injection Rate	Moderate-Fast	

Injection Notes

Zone4 temperature: 330 to 350°C

Zenite® SEA20N

Celanese Corporation - Liquid Crystal Polymer

Notes

¹ Typical properties: these are not to be construed as specifications.

² 10°C/min
