



Zenite® SEA30B

Celanese Corporation - Liquid Crystal Polymer

Sunday, November 3, 2019

General Information

Product Description

Zenite® SEA30B is a 40% mineral filled grade. This grade offers excellent surface appearance, low warpage, and excellent dimensional stability. Application for this grade is compact camera module, and other thin, small electronic parts

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Filler / Reinforcement	• Mineral, 40% Filler by Weight		
Features	• Good Dimensional Stability	• Good Surface Finish	• Low Warpage
Uses	• Camera Applications	• Electrical/Electronic Applications • Thin-walled Parts	

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density	1.85	g/cm ³	ISO 1183
Molding Shrinkage			ISO 294-4
Across Flow	0.90	%	
Flow	0.30	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	1.16E+6	psi	ISO 527-2/1A
Tensile Stress (Break)	14500	psi	ISO 527-2/1A/5
Tensile Strain (Break)	4.3	%	ISO 527-2/1A/5
Flexural Modulus (73°F)	1.16E+6	psi	ISO 178
Flexural Stress (73°F)	16000	psi	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (73°F)	3.3	ft-lb/in ²	ISO 179/1eA
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (66 psi, Unannealed)	504	°F	ISO 75-2/B
Heat Deflection Temperature (264 psi, Unannealed)	428	°F	ISO 75-2/A
Melting Temperature ²	626	°F	ISO 11357-3
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	3.8E+14	ohms	IEC 60093
Volume Resistivity	2.5E+18	ohms·cm	IEC 60093

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	302	°F
Drying Time	6.0	hr
Rear Temperature	554 to 572	°F
Middle Temperature	572 to 590	°F
Front Temperature	617 to 644	°F
Nozzle Temperature	635 to 653	°F
Processing (Melt) Temp	635 to 653	°F
Mold Temperature	212 to 284	°F

Zenite® SEA30B

Celanese Corporation - Liquid Crystal Polymer

Injection	Nominal Value	Unit
Injection Rate	Moderate-Fast	

Injection Notes

Zone4 temperature: 330 to 340°C

Notes

¹ Typical properties: these are not to be construed as specifications.

² 10°C/min