

Synthetic Latices (SBR, XSBR, NBR)

Grades	Total solids % wt	pH	Brookfield viscosity 20 rpm 25°C mPa.s	Emulsifier (1)	Bound styrene % wt	Antioxidant	Main applications
Styrene-Butadiene Latex							
Europrene Latex 5570	66	10.5	800	FA	26	–	Soft foams applications, adhesives, bitumen modification
Europrene Latex 5577	66	10.5	800	FA	30	–	Medium stiffness moulded foams, gel and non-gel carpet foams
Europrene Latex 2430	68	10.5	1100	FA	35	–	High stiffness moulded foams, gel and non-gel carpet foams
Europrene Latex B 010	52	11.5	25	FA	82	–	Reinforcing latex to increase stiffness of soft latex including natural latex
Intex 084	41	11	40	FA	24	–	Fabric impregnation in blend with VPL or natural latex
Intex 131	66	10.3	1000	FA	32	–	Medium stiffness foams, adhesives, bitumen modification
Intex 132	66	10.3	1000	FA	25	–	Soft foams applications, adhesives, bitumen modification
Intex 2720	66	10.3	1000	FA	37	–	High stiffness moulded foams
Intex 2740	66	10.3	1000	FA	40	–	Very high stiffness moulded foams
Carboxylated Styrene-Butadiene Latex							
Europrene Latex 405	50	8	300	SA	40	Non staining	Paper saturation, adhesives
Europrene Latex 406	50	8	300	SA	40	Non staining	Paper saturation
Europrene Latex 440	50	8	300	SA	60	Non staining	Low odour water based adhesives
Europrene Latex 455	50	8	300	SA	47	Non staining	Paper saturation
Europrene Latex 1253	52	8	300	SA	55	Non staining	Synthetic grass backing
Europrene Latex 5583	50	8	300	SA	40	Non staining	Soft handle textile impregnation
Europrene Latex 5584	50	8	400	SA	60	Non staining	Medium-firm handle carpet backsizing and textile impregnation
Europrene Latex 5585	50	8	300	SA	47	Non staining	Soft handle primary and secondary backings
Europrene Latex 5587	50	7.5	600	SA	75	Non staining	Very firm handle textile applications
Europrene Latex 5588	51	8	350	SA	50	Non staining	Soft handle primary backings, anchor coatings and secondary backings
Europrene Latex 8435	50	8	600	SA	69	Non staining	Very firm handle carpet backsizing and needlefelt impregnation
Europrene Latex 8487	50	8	500	SA	67	Non staining	Firm handle carpet backsizing and needlefelt impregnation
Europrene Latex 5595	50	7	400	SA	–	–	Offset and web-offset paper and board coating
Europrene Latex CC 136	50	7	300	SA	–	–	Offset paper and board coating
Acrylonitrile-Butadiene Latex							
Europrene Latex 2620	35	10.5	30	RA	38 *	Non staining	Solvent resistant articles. Specifically designed for beater addition process

(1) FA = Fatty acid
SA = Synthetic anionic

* = ACN

Storage conditions: store in closed, vented tanks at temperatures between 5°C and 30°C.