

Technical Data Sheet



ALCOM CFX ABS 1000 UV 17058 SV1049-17MC

Base Polymer	Acrylonitrile/Butadiene/Styrene/Copolymer
Special Features	metallic effect,UV stabilised
Application Area	injection moulded parts
Typical Applications	housings,clothing / fasteners

Pre-Drying Conditions	80 °C in a dry air (dessiccant) dryer for 2-4 h 80 °C in an air circulating dryer for 3-6 h dependant on moisture content
Processing Injection Moulding	melt temperature 220-260 °C mould temperature 50-80 °C
Storage	dry, protected from light

Properties	Value	Dimension	Test Norm
Mechanical Properties			
Flexural Modulus	2700	MPa	ISO 178
Flexural Stress (3.5% Strain)	71	MPa	ISO 178
Tensile Modulus	2400	MPa	ISO 527
Tensile Stress at Yield	47	MPa	ISO 527
Tensile Elongation at Yield	2.3	%	ISO 527
Tensile Elongation at Break	14	%	ISO 527
Impact Strength (Charpy, 23°C)	90	kJ/m ²	ISO 179/1eU
Impact Strength (Charpy, -40°C)	75	kJ/m ²	ISO 179/1eU
Notched Impact Strength (Charpy, 23°C)	17	kJ/m ²	ISO 179/1eA
Notched Impact Strength (Charpy, -40°C)	6	kJ/m ²	ISO 179/1eA
Thermal Properties			
Vicat B50	96	°C	ISO 306
HDT / A (1,8 MPa)	83	°C	ISO 75-1/-2
Rheological Properties			
Melt Index (MVR)	18	cm ³ /10min	ISO 1133
MVR temperature	220	°C	-
MVR load	10	kg	-
Shrinkage (lengthwise, 24h)	0.5 - 0.7	%	ISO 294-4
Shrinkage (lateral, 24h)	0.4 - 0.6	%	ISO 294-4
Physical Properties			
Density	1050	kg/m ³	ISO 1183