

Technical Data Sheet



ALCOM AWL 109/15 UV WT1217-11LB

Base Polymer	Acrylonitrile/Butadiene/Styrene/Copolymer,modified with Polycarbonate
Filler/Additive System	15 % special filler
Special Features	highly reflective,opaque,UV stabilised,high heat stabilised
Market Segment	Automotive,various
Application Area	lighting,light blocking components
Typical Applications	light guides,reflectors

Pre-Drying Conditions	in a dry air (dessiccant) dryer 80-90 °C for 2-4 h in an air circulating dryer 80-90 °C for 4-8 h max. moisture content <0,02 %
-----------------------	---

Processing Injection Moulding	melt temperature 230-270 °C mould temperature 60-100 °C
-------------------------------	--

Storage	dry, protected from light
---------	---------------------------

Properties	Value	Dimension	Test Norm
Mechanical Properties			
Flexural Modulus	2700	MPa	ISO 178
Flexural Stress (3.5% Strain)	75	MPa	ISO 178
Tensile Modulus	2700	MPa	ISO 527
Tensile Stress at Yield	50	MPa	ISO 527
Tensile Elongation at Yield	3	%	ISO 527
Tensile Elongation at Break	13	%	ISO 527
Impact Strength (Charpy, 23°C)	80	kJ/m ²	ISO 179/1eU
Impact Strength (Charpy, -40°C)	60	kJ/m ²	ISO 179/1eU
Notched Impact Strength (Charpy, 23°C)	13	kJ/m ²	ISO 179/1eA
Notched Impact Strength (Charpy, -40°C)	6.5	kJ/m ²	ISO 179/1eA
Ball Indentation Hardness H358/30	115	MPa	ISO 2039-1
Thermal Properties			
Vicat B50	110	°C	ISO 306
HDT / A (1,8 MPa)	100	°C	ISO 75-1/-2
Rheological Properties			
Melt Index (MVR)	15	cm ³ /10min	ISO 1133
MVR temperature	220	°C	-
MVR load	10	kg	-
Shrinkage (24h)	0.4 - 0.7	%	ISO 294-4
Physical Properties			
Density	1240	kg/m ³	ISO 1183

Technical Data Sheet



ALCOM AWL 109/15 UV WT1217-11LB

(Last update: 03.09.2024)

Flammability

Flammability (1.5 mm)

HB

class

UL 94

Flammability (3.0 mm)

HB

class

UL 94

Optical Properties

Tristimulus Value Y10 of Reflection (d=2,0mm)

92

%

DIN 5033

Tristimulus Value Y10 of Transm.,d=0.5mm


0.4

%

ISO 13468

Diagrams

Spectrum Transmission



Spectrum Reflexion

