

Technical Data Sheet



ALCOLOR PA A BL3102-10

Base Polymer	Polyamide
Colour	blue, similar to RAL 5020
Thermal Stability Colourant	300 °C max.
Light Fastness Colourant	blue woolscale 4
For use in	Polyamide
Special Features	free from cadmium, lead and diarylide pigments, dust-free, high additive content, high dispersibility
Market Segment	various, building and construction
Application Area	injection moulded parts, extruded parts, blow moulded parts

Dosage	2 % injection moulding dependant on wall thickness and required colour intensity
Pre-Drying Conditions	80 °C in a dry air (dessiccant) dryer for 2-12 h dependant on moisture content
Storage	dry, protected from light not above 30°C