

Technical Data Sheet



ALCOLOR PA A YL3051-12

Base Polymer	Polyamide 6
Colour	yellow
Thermal Stability Colourant	280 °C max.
Light Fastness Colourant	blue woolscale 7
For use in	Polyamide 6
Special Features	free from cadmium, lead and diarylide pigments, dust-free, high dispersibility, high additive content
Market Segment	various
Application Area	injection moulded parts, blow moulded parts, extruded parts

Dosage	3 % extrusion 3 % injection moulding dependant on wall thickness and required colour intensity
Pre-Drying Conditions	80 °C in a dry air (dessiccant) dryer for 2-12 h
Storage	dry, protected from light not above 30°C