

Technical Data Sheet



ALTECH PA6 A 2030/326 GF30 UV

Base Polymer	Polyamide 6
Filler/Additive System	30 % glass fibres
Colour	red
Special Features	UV stabilised,processing stabilised,nucleated
Market Segment	Automotive,Machinery,building and construction,sport and leisure
Application Area	injection moulded parts,electrical components,exterior parts,interior decoration / finishing
Typical Applications	housings,clothing / fasteners,functional components

Pre-Drying Conditions	80 °C in a dry air (dessiccant) dryer for 2-12 h dependant on moisture content max. moisture content <0,15 %
-----------------------	---

Processing Injection Moulding	melt temperature 270-290 °C mould temperature 80-100 °C
-------------------------------	--

Storage	dry, protected from light
---------	---------------------------

Properties	dry/cond.	Dimension	Test Norm
Mechanical Properties			
Flexural Modulus	8800 / 5400	MPa	ISO 178
Flexural Strength	225 / 140	MPa	ISO 178
Tensile Modulus	9800 / 6000	MPa	ISO 527
Tensile Strength at Break	150 / 85	MPa	ISO 527
Tensile Elongation at Break	2.4 / 5.1	%	ISO 527
Impact Strength (Charpy, 23°C)	50 / 60	kJ/m ²	ISO 179/1eU
Impact Strength (Charpy, -40°C)	40 / -	kJ/m ²	ISO 179/1eU
Notched Impact Strength (Charpy, 23°C)	7 / 10	kJ/m ²	ISO 179/1eA
Notched Impact Strength (Charpy, -40°C)	5.5 / -	kJ/m ²	ISO 179/1eA
Thermal Properties			
HDT / A (1,8 MPa)	210 / *	°C	ISO 75-1/-2
DSC (Melt Point)	221 / *	°C	ISO 11357
Rheological Properties			
Shrinkage (lengthwise, 24h)	0.2 - 0.4	%	ISO 294-4
Shrinkage (lateral, 24h)	0.6 - 0.8	%	ISO 294-4
Physical Properties			
Density	1390 / -	kg/m ³	ISO 1183