

Technical Data Sheet



ALCOM PA66 910/1 GF30 TF15 UV

Base Polymer	Polyamide 66
Filler/Additive System	30 % glass fibres, 15 % PTFE, highly UV stabilised
Special Features	improved sliding / wear, heat stabilised
Market Segment	Automotive, Machinery
Application Area	injection moulded parts
Typical Applications	functional components, bearings and sliding elements

Pre-Drying Conditions in a dry air (dessiccant) dryer <80 °C
for 2-12 h
dependant on moisture content

Processing Injection Moulding melt temperature 280-300 °C
mould temperature 80-120 °C

Storage dry, protected from light

Properties	dry/cond.	Dimension	Test Norm
Mechanical Properties			
Flexural Modulus	8700 / -	MPa	ISO 178
Flexural Strength	230 / -	MPa	ISO 178
Tensile Modulus	9800 / -	MPa	ISO 527
Tensile Strength at Break	160 / -	MPa	ISO 527
Tensile Elongation at Break	2.8 / -	%	ISO 527
Impact Strength (Charpy, 23°C)	70 / -	kJ/m ²	ISO 179/1eU
Impact Strength (Charpy, -40°C)	50 / -	kJ/m ²	ISO 179/1eU
Notched Impact Strength (Charpy, 23°C)	10 / -	kJ/m ²	ISO 179/1eA
Notched Impact Strength (Charpy, -40°C)	8 / -	kJ/m ²	ISO 179/1eA
Thermal Properties			
HDT / A (1,8 MPa)	250 / *	°C	ISO 75-1/-2
DSC (Melt Point)	263 / *	°C	ISO 11357
Rheological Properties			
Shrinkage (lengthwise, 24h)	0.2 - 0.4	%	ISO 294-4
Shrinkage (lateral, 24h)	0.6 - 0.8	%	ISO 294-4
Physical Properties			
Density	1480 / -	kg/m ³	ISO 1183