

Technical Data Sheet - Preliminary Product



ALCOLOR PC A GY937-4136

Base Polymer	Polycarbonate
Colour	grey, similar to RAL 7005
Thermal Stability Colourant	280 °C max.
Light Fastness Colourant	blue woolscale 5
For use in	Polycarbonate
Special Features	free from cadmium, lead and diarylide pigments, dust-free, high dispersibility, high additive content
Market Segment	electrical and electronic, Furniture, building and construction, sport and leisure
Application Area	injection moulded parts, blow moulded parts, extruded parts, compounding

Dosage	5,0 % extrusion 5,0 % injection moulding dependant on wall thickness and required colour intensity dependant on application and operational area
--------	---

Pre-Drying Conditions	120 °C in a dry air (dessiccant) dryer for 2-3 h 120 °C in an air circulating dryer for 4-12 h max. moisture content <0,02 %
-----------------------	--

Processing Injection Moulding	melt temperature 270-310 °C mould temperature 80-110 °C
-------------------------------	--

Storage	dry, protected from light tightly sealed
---------	---