

Technical Data Sheet



ALCOLOR PC BK5216-18TR

Base Polymer	Polycarbonate
Colour	black
Thermal Stability Colourant	300 °C max.
Light Fastness Colourant	blue woolscale 8
For use in	Polycarbonate
Special Features	free from cadmium, lead and diarylide pigments, dust-free, high dispersibility, high additive content
Market Segment	electrical and electronic, Furniture, building and construction, sport and leisure
Application Area	injection moulded parts, blow moulded parts, extruded parts

Dosage	2,0 % extrusion 2,0 % injection moulding dependant on application and operational area
--------	--

Pre-Drying Conditions	120 °C in a dry air (dessiccant) dryer for 2-3 h 120 °C in an air circulating dryer for 4-12 h dependant on moisture content
-----------------------	--

Processing Injection Moulding	melt temperature 270-310 °C mould temperature 80-110 °C
-------------------------------	--

Storage	dry, protected from light
---------	---------------------------