

Technical Data Sheet - Preliminary Product



ALCOM LB ECO PC 1000 17152 UV IM WT2083-07

Base Polymer	Polycarbonate
Special Features	impact modified,UV stabilised,contains recycled material
Market Segment	electrical and electronic,Lighting,various
Application Area	lamps,light blocking components,various
Typical Applications	light guides,lamps,sockets,various

Pre-Drying Conditions	120 °C in a dry air (dessiccant) dryer for 2-4 h 120 °C in an air circulating dryer for 4-12 h max. moisture content <0,02 %
-----------------------	--

Processing Injection Moulding	melt temperature 270-310 °C mould temperature 80-110 °C
-------------------------------	--

Storage	dry, protected from light
---------	---------------------------

Properties	Value	Dimension	Test Norm
Mechanical Properties			
Tensile Modulus	2500	MPa	ISO 527
Tensile Stress at Yield	57	MPa	ISO 527
Tensile Elongation at Yield	5.7	%	ISO 527
Tensile Elongation at Break	50	%	ISO 527
Impact Strength (Charpy, 23°C)	no break	kJ/m ²	ISO 179/1eU
Notched Impact Strength (Charpy, 23°C)	40	kJ/m ²	ISO 179/1eA
Thermal Properties			
Vicat B50	140	°C	ISO 306
Rheological Properties			
Melt Index (MVR)	17	cm ³ /10min	ISO 1133
MVR temperature	300	°C	-
MVR load	1.2	kg	-
Shrinkage (24h)	0.7 - 0.9	%	ISO 294-4
Physical Properties			
Density	1250	kg/m ³	ISO 1183
Flammability			
Flammability (1.5 mm)	V-2	class	UL 94
Glow Wire (GWFI, 850°C, 2.0mm)	passed	-	DIN EN 60695