

Technical Data Sheet



ALCOM LD2 PC 1000 17150 UV GY2240-08

Base Polymer	Polycarbonate
Special Features	impact modified,UV stabilised,contains recycled material,light scattering
Market Segment	electrical and electronic,Lighting,various
Application Area	exterior parts,fixtures / fittings,electrical components
Typical Applications	housings,lamps,sockets,various
Approvals	GS93016

Pre-Drying Conditions	120 °C in a dry air (dessiccant) dryer for 2-4 h 120 °C in an air circulating dryer for 4-12 h max. moisture content <0,02 %
-----------------------	--

Processing Injection Moulding	melt temperature 270-310 °C mould temperature 80-110 °C
-------------------------------	--

Storage	dry, protected from light
---------	---------------------------

Properties	Value	Dimension	Test Norm
Mechanical Properties			
Flexural Modulus	2450	MPa	ISO 178
Flexural Stress (3.5% Strain)	75	MPa	ISO 178
Tensile Modulus	2300	MPa	ISO 527
Tensile Stress at Yield	63	MPa	ISO 527
Tensile Elongation at Yield	6	%	ISO 527
Tensile Elongation at Break	100	%	ISO 527
Impact Strength (Charpy, 23°C)	no break	kJ/m ²	ISO 179/1eU
Impact Strength (Charpy, -40°C)	no break	kJ/m ²	ISO 179/1eU
Notched Impact Strength (Charpy, 23°C)	75	kJ/m ²	ISO 179/1eA
Notched Impact Strength (Charpy, -40°C)	12	kJ/m ²	ISO 179/1eA
Thermal Properties			
Vicat B50	146	°C	ISO 306
HDT / A (1,8 MPa)	128	°C	ISO 75-1/-2
Rheological Properties			
Melt Index (MVR)	15	cm ³ /10min	ISO 1133
MVR temperature	300	°C	-
MVR load	1.2	kg	-
Shrinkage (24h)	0.6 - 0.9	%	ISO 294-4
Physical Properties			
Density	1190	kg/m ³	ISO 1183

Technical Data Sheet



ALCOM LD2 PC 1000 17150 UV GY2240-08

Flammability

Glow Wire (GWFI, 850 °C, 2.0mm)	passed	-	DIN EN 60695
---------------------------------	--------	---	--------------

Optical Properties

Total Transmission T(Y) (d=1,0mm, A, 2°)	77	%	ISO 13468
Total Transmission T(Y) (d=2,0mm, A, 2°)	66	%	ISO 13468
Total Transmission T(Y) (d=3,0mm, A, 2°)	56	%	ISO 13468
Total Transmission T(Y) (d=4,0mm, A, 2°)	48	%	ISO 13468
Haze T(Y) (d=1,0 mm, A, 2°)	2.5	%	ISO 13468
Haze T(Y) (d=2,0 mm, A, 2°)	3	%	ISO 13468
Haze T(Y) (d=3,0 mm, A, 2°)	4	%	ISO 13468
Haze T(Y) (d=4,0 mm, A, 2°)	5	%	ISO 13468
Half Power Angle T(Y) (d=1,0mm, A, 2°)	1	°	-
Half Power Angle T(Y) (d=2,0mm, A, 2°)	1	°	-
Half Power Angle T(Y) (d=3,0mm, A, 2°)	1	°	-
Half Power Angle T(Y) (d=4,0mm, A, 2°)	1	°	-