

Technical Data Sheet



ALCOM LD2 PC 1000 UV 14019 WT1030-14

Base Polymer	Polycarbonate
Filler/Additive System	special filler, UV stabilised
Special Features	translucent, light scattering, high light diffusion
Market Segment	Automotive, Lighting
Application Area	lighting, light transparent components, injection moulded parts
Typical Applications	lamp covers, display elements, operating elements
Approvals	GS93016

Pre-Drying Conditions	120 °C in a dry air (dessiccant) dryer for 2-4 h 120 °C in an air circulating dryer for 4-12 h max. moisture content <0,02 %
Processing Injection Moulding	melt temperature 270-310 °C mould temperature 80-110 °C
Storage	dry, protected from light

Properties	Value	Dimension	Test Norm
Mechanical Properties			
Flexural Modulus	2450	MPa	ISO 178
Flexural Stress (3.5% Strain)	76	MPa	ISO 178
Tensile Modulus	2400	MPa	ISO 527
Tensile Stress at Yield	66	MPa	ISO 527
Tensile Elongation at Yield	6	%	ISO 527
Tensile Elongation at Break	70	%	ISO 527
Impact Strength (Charpy, 23°C)	no break	kJ/m ²	ISO 179/1eU
Impact Strength (Charpy, -40°C)	no break	kJ/m ²	ISO 179/1eU
Notched Impact Strength (Charpy, 23°C)	12	kJ/m ²	ISO 179/1eA
Notched Impact Strength (Charpy, -40°C)	12	kJ/m ²	ISO 179/1eA
Thermal Properties			
Vicat B50	142	°C	ISO 306
HDT / A (1,8 MPa)	124	°C	ISO 75-1/-2
Rheological Properties			
Melt Index (MVR)	16	cm ³ /10min	ISO 1133
MVR temperature	300	°C	-
MVR load	1.2	kg	-
Shrinkage (24h)	0.6 - 0.9	%	ISO 294-4
Physical Properties			
Density	1190	kg/m ³	ISO 1183

Technical Data Sheet



ALCOM LD2 PC 1000 UV 14019 WT1030-14

Flammability

Flammability (0.75 mm)

Flammability (1.5 mm)

Glow Wire (GWFI, 850 °C, 1.0mm)

Glow Wire (GWFI, 850 °C, 2.0mm)

V-2

class

UL 94

HB

class

UL 94

passed

-

DIN EN 60695

passed

-

DIN EN 60695

Optical Properties

Total Transmission T(Y) (d=1,0mm, A, 2°)

20

%

ISO 13468

Total Transmission T(Y) (d=2,0mm, A, 2°)

9

%

ISO 13468

Total Transmission T(Y) (d=3,0mm, A, 2°)

4

%

ISO 13468

Haze T(Y) (d=1,0 mm, A, 2°)

95

%

ISO 13468

Haze T(Y) (d=2,0 mm, A, 2°)

95

%

ISO 13468

Haze T(Y) (d=3,0 mm, A, 2°)

95

%

ISO 13468

Half Power Angle T(Y) (d=1,0mm, A, 2°)

56

°

-

Half Power Angle T(Y) (d=2,0mm, A, 2°)

58

°

-

Half Power Angle T(Y) (d=3,0mm, A, 2°)


58

°


-

Diagrams

Stress-Strain



Angle dependent relative irradiance



Technical Data Sheet

Alcom[®]

MOCOM

ALCOM LD2 PC 1000 UV 14019 WT1030-14

Spectrum

