

Technical Data Sheet



ALCOM PC 730/3.1 UV WT1283-09LDM

Base Polymer	Polycarbonate
Filler/Additive System	special filler, UV stabilised, antioxidant
Special Features	low gloss, light scattering, high viscosity, extrusion grade
Market Segment	Lighting
Application Area	lighting, light transparent components
Typical Applications	lamp covers

Pre-Drying Conditions	120 °C in a dry air (dessiccant) dryer for 2-4 h 120 °C in an air circulating dryer for 4-12 h max. moisture content <0,02 %
-----------------------	--

Processing Extrusion	melt temperature 240-280 °C
----------------------	-----------------------------

Storage	dry, protected from light
---------	---------------------------

Properties	Value	Dimension	Test Norm
Mechanical Properties			
Flexural Modulus	2550	MPa	ISO 178
Flexural Stress (3.5% Strain)	79	MPa	ISO 178
Tensile Modulus	2400	MPa	ISO 527
Tensile Stress at Yield	68	MPa	ISO 527
Tensile Elongation at Yield	5.8	%	ISO 527
Tensile Elongation at Break	25	%	ISO 527
Impact Strength (Charpy, 23°C)	no break	kJ/m ²	ISO 179/1eU
Impact Strength (Charpy, -40°C)	85	kJ/m ²	ISO 179/1eU
Notched Impact Strength (Charpy, 23°C)	4	kJ/m ²	ISO 179/1eA
Notched Impact Strength (Charpy, -40°C)	4	kJ/m ²	ISO 179/1eA
Thermal Properties			
Vicat B50	135	°C	ISO 306
HDT / A (1,8 MPa)	122	°C	ISO 75-1/-2
Rheological Properties			
Melt Index (MVR)	8	cm ³ /10min	ISO 1133
MVR temperature	300	°C	-
MVR load	1.2	kg	-
Shrinkage (24h)	0.8 - 1.1	%	ISO 294-4
Physical Properties			
Density	1190	kg/m ³	ISO 1183

Technical Data Sheet



ALCOM PC 730/3.1 UV WT1283-09LDM

Flammability

Flammability (0.75 mm)	HB	class	UL 94
Yellow Card available	yes	-	-
Flammability (1.5 mm)	HB	class	UL 94
Yellow Card available	yes	-	-
Glow Wire (GWFI, 850 °C, 1.0mm)	passed	-	DIN EN 60695
Glow Wire (GWFI, 850 °C, 2.0mm)	passed	-	DIN EN 60695

Optical Properties

Total Transmission T(Y) (d=1,0mm, A, 2°)	82	%	ISO 13468
Total Transmission T(Y) (d=2,0mm, A, 2°)	70	%	ISO 13468
Total Transmission T(Y) (d=3,0mm, A, 2°)	58	%	ISO 13468
Total Transmission T(Y) (d=4,0mm, A, 2°)	51	%	ISO 13468
Haze T(Y) (d=1,0 mm, A, 2°)	93	%	ISO 13468
Haze T(Y) (d=2,0 mm, A, 2°)	95	%	ISO 13468
Haze T(Y) (d=3,0 mm, A, 2°)	95	%	ISO 13468
Haze T(Y) (d=4,0 mm, A, 2°)	95	%	ISO 13468
Half Power Angle T(Y) (d=1,0mm, A, 2°)	6	°	-
Half Power Angle T(Y) (d=2,0mm, A, 2°)	21	°	-
Half Power Angle T(Y) (d=3,0mm, A, 2°)	34	°	-
Half Power Angle T(Y) (d=4,0mm, A, 2°)	43	°	-