

Technical Data Sheet



ALCOM PC 740/2813P.1 CF

Base Polymer	Polycarbonate
Filler/Additive System	10 % carbon fibres
Special Features	electrically conductive, reduced surface resistivity, impact modified
Market Segment	Machinery, Automotive
Application Area	injection moulded parts
Typical Applications	housings, functional components

Pre-Drying Conditions 120 °C in a dry air (dessiccant) dryer
for 2-4 h
max. moisture content <0,02 %

Processing Injection Moulding melt temperature 290-330 °C
mould temperature 80-130 °C

Storage dry, protected from light

Properties	Value	Dimension	Test Norm
Mechanical Properties			
Flexural Modulus	6800	MPa	ISO 178
Flexural Strength	160	MPa	ISO 178
Tensile Modulus	7800	MPa	ISO 527
Tensile Strength at Break	108	MPa	ISO 527
Tensile Elongation at Break	2.9	%	ISO 527
Impact Strength (Charpy, 23°C)	40	kJ/m ²	ISO 179/1eU
Impact Strength (Charpy, -40°C)	40	kJ/m ²	ISO 179/1eU
Notched Impact Strength (Charpy, 23°C)	9	kJ/m ²	ISO 179/1eA
Notched Impact Strength (Charpy, -40°C)	7.5	kJ/m ²	ISO 179/1eA
Thermal Properties			
Vicat B50	148	°C	ISO 306
HDT / A (1,8 MPa)	143	°C	ISO 75-1/-2
Electrical Properties			
Surface Resistance	1000	Ohm	IEC 62631-3-2
Rheological Properties			
Shrinkage (lengthwise, 24h)	0.1 - 0.3	%	ISO 294-4
Shrinkage (lateral, 24h)	0.3 - 0.5	%	ISO 294-4
Physical Properties			
Density	1230	kg/m ³	ISO 1183