

Technical Data Sheet



ALTECH PC A 1000/269 UV

Base Polymer	Polycarbonate
Filler/Additive System	light stabiliser
Colour	black,blue,green,natural color,orange,red,white
Special Features	easy release (demoulding),good flow,processing stabilised,UV stabilised,injection moulding grade
Market Segment	Automotive,Machinery,building and construction
Application Area	electrical components
Typical Applications	housings,operating elements

Pre-Drying Conditions	in a dry air (dessiccant) dryer 100-120 °C for 2-3 h in an air circulating dryer 100-120 °C for 4-12 h max. moisture content <0,02 %
-----------------------	--

Processing Injection Moulding	melt temperature 270-310 °C mould temperature 80-110 °C
-------------------------------	--

Storage	dry, protected from light
---------	---------------------------

Properties	Value	Dimension	Test Norm
Mechanical Properties			
Tensile Modulus	2400	MPa	ISO 527
Tensile Stress at Yield	65	MPa	ISO 527
Tensile Elongation at Yield	6	%	ISO 527
Tensile Elongation at Break	70	%	ISO 527
Impact Strength (Charpy, 23°C)	no break	kJ/m ²	ISO 179/1eU
Impact Strength (Charpy, -40°C)	no break	kJ/m ²	ISO 179/1eU
Notched Impact Strength (Charpy, 23°C)	11	kJ/m ²	ISO 179/1eA
Notched Impact Strength (Charpy, -40°C)	10	kJ/m ²	ISO 179/1eA
Thermal Properties			
Vicat B50	143	°C	ISO 306
Rheological Properties			
Melt Index (MVR)	20	cm ³ /10min	ISO 1133
MVR temperature	300	°C	-
MVR load	1.2	kg	-
Shrinkage (24h)	0.7 - 0.9	%	ISO 294-4
Physical Properties			
Density	1190	kg/m ³	ISO 1183