

Technical Data Sheet



ALTECH PP-H A 1000/578

Base Polymer	Polypropylene Homopolymer
Colour	grey,yellow
Application Area	various
Typical Applications	various

Pre-Drying Conditions	in a dry air (dessiccant) dryer 80-120 °C for 2-3 h in an air circulating dryer 80-120 °C for 2-4 h dependant on moisture content max. moisture content <0,10 %
-----------------------	--

Processing Injection Moulding	melt temperature 200-270 °C mould temperature 20-90 °C
-------------------------------	---

Storage	dry, protected from light
---------	---------------------------

Properties	Value	Dimension	Test Norm
Mechanical Properties			
Flexural Modulus	1500	MPa	ISO 178
Flexural Stress (3.5% Strain)	36	MPa	ISO 178
Tensile Modulus	1600	MPa	ISO 527
Tensile Stress at Yield	36	MPa	ISO 527
Tensile Elongation at Yield	9.4	%	ISO 527
Tensile Elongation at Break	80	%	ISO 527
Impact Strength (Charpy, 23°C)	135	kJ/m ²	ISO 179/1eU
Impact Strength (Charpy, -40°C)	16	kJ/m ²	ISO 179/1eU
Notched Impact Strength (Charpy, 23°C)	6	kJ/m ²	ISO 179/1eA
Notched Impact Strength (Charpy, -40°C)	1.5	kJ/m ²	ISO 179/1eA
Thermal Properties			
Vicat B50	90	°C	ISO 306
HDT / A (1,8 MPa)	58	°C	ISO 75-1/-2
DSC (Melt Point)	163	°C	ISO 11357
Rheological Properties			
Melt Index (MVR)	2.5	cm ³ /10min	ISO 1133
MVR temperature	230	°C	-
MVR load	2.16	kg	-
Shrinkage (lengthwise, 24h)	1.6 - 2	%	ISO 294-4
Shrinkage (lateral, 24h)	1.5 - 1.9	%	ISO 294-4
Physical Properties			
Density	910	kg/m ³	ISO 1183