

Technical Data Sheet



ALTECH PP-H A 2030/157.01 GF30

Base Polymer	Polypropylene Homopolymer
Filler/Additive System	30 % glass fibres
Colour	black
Special Features	chemically coupled,heat stabilised,easy flow
Market Segment	Automotive,electrical and electronic,Machinery
Typical Applications	housings,fixing elements

Pre-Drying Conditions	in an air circulating dryer 80-120 °C for 2-4 h in a dry air (dessiccant) dryer 80-120 °C for 2-3 h dependant on moisture content max. moisture content <0,10 %
-----------------------	--

Processing Injection Moulding	melt temperature 200-250 °C mould temperature 20-70 °C
-------------------------------	---

Storage	dry, protected from light
---------	---------------------------

Properties	Value	Dimension	Test Norm
Mechanical Properties			
Flexural Modulus	5800	MPa	ISO 178
Flexural Strength	130	MPa	ISO 178
Tensile Modulus	7000	MPa	ISO 527
Tensile Strength at Break	87	MPa	ISO 527
Tensile Elongation at Break	2.9	%	ISO 527
Impact Strength (Charpy, 23°C)	50	kJ/m ²	ISO 179/1eU
Impact Strength (Charpy, -40°C)	25	kJ/m ²	ISO 179/1eU
Notched Impact Strength (Charpy, 23°C)	9.5	kJ/m ²	ISO 179/1eA
Notched Impact Strength (Charpy, -40°C)	7	kJ/m ²	ISO 179/1eA
Thermal Properties			
Vicat B50	136	°C	ISO 306
HDT / A (1,8 MPa)	155	°C	ISO 75-1/-2
DSC (Melt Point)	166	°C	ISO 11357
Rheological Properties			
Melt Index (MVR)	17	cm ³ /10min	ISO 1133
MVR temperature	230	°C	-
MVR load	2.16	kg	-
Shrinkage (lengthwise, 24h)	0.2 - 0.4	%	ISO 294-4
Shrinkage (lateral, 24h)	0.5 - 0.7	%	ISO 294-4
Physical Properties			
Density	1120	kg/m ³	ISO 1183