

Technical Data Sheet

❖ **Alfater XL[®]****MOCOM****ALFATER XL A65I 2GP0000**

Base Polymer	Thermoplastic Vulcanisate (PP+EPDM)
Colour	natural color,black
Service Temperature	max. range (depending on load, geometry, etc.) -40-125 °C
Special Features	good recovery,good weathering resistance,good chemical resistance,good ozone resistance,good hot air resistance,good hydrolysis resistant
Market Segment	Automotive,building and construction,do-it-yourself,electrical and electronic,Machinery,Furniture
Application Area	injection moulded parts
Typical Applications	seals,sealing lip,handles,soft touch elements,impact protection / shock absorber,protection caps,cable ducts,casters,plugs,fastener & connector,2K components
Adhesion to	Polypropylene Homopolymer,Polypropylene Copolymer,Polyethylene,Thermoplastic Vulcanisate (PP+EPDM),Thermoplastic Olefin Elastomer,Thermoplastic Elastomer general

Pre-Drying Conditions	in a dry air (dessiccant) dryer 60-70 °C for 2-4 h max. moisture content <0,10 %
Processing Injection Moulding	melt temperature 195-230 °C mould temperature 10-60 °C injection speed high back pressure (hydraulic) >5 bar holding pressure 50-70% of injection pressure
Storage	dry, protected from light not above 30°C tightly sealed do not stack the pallets

Properties	Value	Dimension	Test Norm
Mechanical Properties			
Tensile Stress at 100% Elongation (Type 2)	2.7	MPa	ISO 37
Tensile Strength (Type 2)	5.6	MPa	ISO 37
Tear Strength (Method Ba)	26	kN/m	ISO 34-1
Elongation at Break (Type 2)	375	%	ISO 37
Shore Hardness A (15s)	65	-	ISO 868
Thermal Properties			
Coeff. of Linear Therm. Expansion (parallel)	10	E-6/K	ISO 11359-1/-2
Coeff. of Linear Therm. Expansion (normal)	18.8	E-6/K	ISO 11359-1/-2
Compression Set (22h / 100 °C / 25% / Type A)	42	%	ISO 815
Compression Set (22h / 70 °C / 25% / Type A)	35	%	ISO 815
Compression Set (72h / 22 °C / 25% / Type A)	25	%	ISO 815

Technical Data Sheet

❖ Alfater XL[®]

MOCOM

ALFATER XL A65I 2GP0000

Compression Set (72h / 125°C / 25% / Type A)	55	%	ISO 815
Electrical Properties			
Tracking Resistance (CTI)	600	-	IEC 60112
Rheological Properties			
Shrinkage (lengthwise, 24h)	2.5 - 2.9	%	ISO 294-4
Shrinkage (lateral, 24h)	1.3 - 1.7	%	ISO 294-4
Spiral Flow (2 mm wall thickness)	35	cm	-
Physical Properties			
Density	900	kg/m ³	ISO 1183
Ageing Properties			
Ozone resistance (method A)	passed	-	ISO 1431-1A

Diagrams

Specific volume-temperature (pvT)

