

Technical Data Sheet

❖ Alfater XL[®]

MOCOM

ALFATER XL D40I 2GP0050

Base Polymer	Thermoplastic Vulcanisate (PP+EPDM)
Colour	natural color,black
Service Temperature	max. range (depending on load, geometry, etc.) -40-125 °C
Special Features	good recovery,good weathering resistance,good chemical resistance,good ozone reistance,good hot air resistance,good hydrolysis resistant
Market Segment	Automotive,building and construction,do-it-yourself,electrical and electronic,Machinery,Furniture
Application Area	injection moulded parts
Typical Applications	seals,sealing lip,handles,impact protection / shock absorber,protection caps,cable ducts,casters,plugs,fastener & connector,2K components
Adhesion to	Polypropylene Homopolymer,Polypropylene Copolymer,Polyethylene,Thermoplastic Vulcanisate (PP+EPDM),Thermoplastic Olefin Elastomer,Thermoplastic Elastomer general

Pre-Drying Conditions	in a dry air (dessiccant) dryer 70-80 °C for 2-4 h max. moisture content <0,10 %
Processing Injection Moulding	melt temperature 200-240 °C mould temperature 10-70 °C injection speed high back pressure (hydraulic) holding pressure 50-70% of injection pressure
Storage	dry, protected from light tightly sealed

Properties	Value	Dimension	Test Norm
Mechanical Properties			
Tensile Stress at 100% Elongation (Type 2)	10.5	MPa	ISO 37
Tensile Strength (Type 2)	16.5	MPa	ISO 37
Tear Strength (Method Ba)	75	kN/m	ISO 34-1
Elongation at Break (Type 2)	570	%	ISO 37
Shore Hardness D (15s)	40	-	ISO 868
Thermal Properties			
Compression Set (22h / 100 °C / 25% / Type A)	77	%	ISO 815
Compression Set (22h / 70 °C / 25% / Type A)	67	%	ISO 815
Compression Set (72h / 22 °C / 25% / Type A)	47	%	ISO 815
Compression Set (72h / 125 °C / 25% / Type A)	92	%	ISO 815
Electrical Properties			
Tracking Resistance (CTI)	600	-	IEC 60112

Technical Data Sheet

❖ Alfater XL[®]

MOCOM

ALFATER XL D40I 2GP0050

Rheological Properties

Shrinkage (lengthwise, 24h)	1.3 - 1.7	%	ISO 294-4
Shrinkage (lateral, 24h)	0.9 - 1.3	%	ISO 294-4
Spiral Flow (2 mm wall thickness)	40	cm	-

Physical Properties

Density	960	kg/m ³	ISO 1183
---------	-----	-------------------	----------

Ageing Properties

Ozone resistance (method A)	passed	-	ISO 1431-1A
-----------------------------	--------	---	-------------

Diagrams

Specific volume-temperature (pvT)

